

EN 29053 - Determination of airflow resistance

Direct airflow method - method A


Client: Kinnasand

Date: 12-12-19

Type: Journey 100% Trevira CS
Colour: 16
Order:
Batch:
Manufacturer: Kinnasand

Specimen Diameter: 100 mm
Thickness: 0.51 mm
Area specific mass: 287 g/m²

u_l (mm/s)	$R_{s,l}$ (Pa s/m)
14.16	1190
11.80	1192
9.44	1194
7.12	1189
4.42	1256
2.46	1118



Airflow Resistance

$R_s = 1245$ Pa s/m