

# EN 29053 - Determination of airflow resistance

Direct airflow method - method A


Client: Kinnasand

Date: 12-12-19

Type: Site 100% Polyester FR  
Colour: 33  
Order:  
Batch:  
Manufacturer: Kinnasand

Specimen Diameter: 100 mm  
Thickness: 0.34 mm  
Area specific mass: 124 g/m<sup>2</sup>

$u_l$ (mm/s)	$R_{s,l}$ (Pa s/m)
16.53	1
14.16	2
11.80	4
9.44	5
7.12	7
4.42	9



**Airflow Resistance**

**$R_s = 12$  Pa s/m**