

# Test Report

Report Number:  
994395-4-TEX



**DANISH  
TECHNOLOGICAL  
INSTITUTE**

Gregersensvej 1  
DK-2630 Taastrup  
+45 72 20 20 00  
info@teknologisk.dk  
www.teknologisk.dk

Page 1 of 6  
Init.: CHF/LELN  
Order no.: 994395  
Encl.: 0

**Assignor:** Kinnasand GmbH, Danziger Strasse 6 , D-26655 Westerstede, Germany

**Material:** Samples of curtain fabric designated: Erin II by kinnasand. See page 2 for detailed sample description.

**Sampling:** The assignor confirms having selected the product. The product was forwarded by the assignor and received at Danish Technological Institute on 20 September 2021.

**Period:** The test took place from 21 September 2021 to 18 October 2021.

**Method:** The test methods used are referenced in connection with the results. See page 6.

**Test results:** The results are shown on page 6.

**Terms:** This test was conducted accredited in accordance with international requirements (ISO/IEC 17025:2017) and in accordance with the General Terms and Conditions of Danish Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent.

**Place:** Danish Technological Institute, Taastrup, Environmental Technology

**Signature:** This document is only valid with a digital signature from Danish Technological Institute. The date of issue appears from the digital signature.  
  
Charlotte Fischer  
Senior Consultant



DIGITALLY SIGNED DOCUMENT

20 October 2021

DANISH TECHNOLOGICAL INSTITUTE



**DANAK**

TEST Reg.no. 2







## Samples

Sample mark	Description	Photo
1	Sample of curtain fabric Designated: Erin II by Kinnasand	
2	Sample of curtain fabric Designated: Erin II by Kinnasand	
3	Sample of curtain fabric Designated: Erin II by Kinnasand	
5	Sample of curtain fabric Designated: Erin II by Kinnasand	
6	Sample of curtain fabric Designated: Erin II by Kinnasand	








## Samples (*continued*)

Sample mark	Description	Photo
11	Sample of curtain fabric Designated: Erin II by Kinnasand	
12	Sample of curtain fabric Designated: Erin II by Kinnasand	
13	Sample of curtain fabric Designated: Erin II by Kinnasand	
14	Sample of curtain fabric Designated: Erin II by Kinnasand	
16	Sample of curtain fabric Designated: Erin II by Kinnasand	





## Samples (*continued*)

Sample mark	Description	Photo
21	Sample of curtain fabric Designated: Erin II by Kinnasand	
24	Sample of curtain fabric Designated: Erin II by Kinnasand	
25	Sample of curtain fabric Designated: Erin II by Kinnasand	
26	Sample of curtain fabric Designated: Erin II by Kinnasand	
31	Sample of curtain fabric Designated: Erin II by Kinnasand	



## Samples (*continued*)

Sample mark	Description	Photo
33	Sample of curtain fabric Designated: Erin II by Kinnasand	
43	Sample of curtain fabric Designated: Erin II by Kinnasand	



## Results

### *Test of Samples of curtain fabric designated: Erin II by kinnasand*

---

#### Colour fastness to artificial light: Xenon arc fading lamp test

EN ISO 105-B02:2014 Method 2

1-8 scale, 8 best rating

Test apparatus: Atlas Ci4000 Xenon Weather-Ometer

Sample mark	Colour fastness
1	7
2	7
3	7
5	7
6	5-6
11	6
12	5
13	6
14	6
16	5-6
21	6
24	4-5
25	5-6
26	6
31	6
33	6
43	6-7

---