

Test Report

Report Number:
994395-10-TEX



**DANISH
TECHNOLOGICAL
INSTITUTE**

Gregersensvej 1
DK-2630 Taastrup
+45 72 20 20 00
info@teknologisk.dk
www.teknologisk.dk

Page 1 of 3
Init.: CHF/LELN
Order no.: 994395
Encl.: 0

Assignor: Kinnasand GmbH, Danziger Strasse 6 , D-26655 Westerstede, Germany

Material: Samples of curtain fabric designated: Mori by kinnasand. See page 2 for detailed sample description.

Sampling: The assignor confirms having selected the product. The product was forwarded by the assignor and received at Danish Technological Institute on 20 September 2021.

Period: The test took place from 21 September 2021 to 18 October 2021.

Method: The test methods used are referenced in connection with the results. See page 3.

Test results: The results are shown on page 3.

Terms: This test was conducted accredited in accordance with international requirements (ISO/IEC 17025:2017) and in accordance with the General Terms and Conditions of Danish Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent.

Place: Danish Technological Institute, Taastrup, Environmental Technology

Signature: This document is only valid with a digital signature from Danish Technological Institute. The date of issue appears from the digital signature.

Charlotte Fischer
Senior Consultant



DIGITALLY SIGNED DOCUMENT

20 October 2021

DANISH TECHNOLOGICAL INSTITUTE








DANAK

TEST Reg.no. 2



Samples

Sample mark	Description	Photo
1	Sample of curtain fabric Designated: Mori by Kinnasand	
6	Sample of curtain fabric Designated: Mori by Kinnasand	
13	Sample of curtain fabric Designated: Mori by Kinnasand	
14	Sample of curtain fabric Designated: Mori by Kinnasand	
20	Sample of curtain fabric Designated: Mori by Kinnasand	



Results

Test of Samples of curtain fabric designated: Mori by kinnasand

Colour fastness to artificial light: Xenon arc fading lamp test

EN ISO 105-B02:2014 Method 2

1-8 scale, 8 best rating

Test apparatus: Atlas Ci4000 Xenon Weather-Ometer

Sample mark	Colour fastness
1	7
6	7
13	7
14	7
20	7
