

Test Report

Report Number:
981419-1-TEX



**DANISH
TECHNOLOGICAL
INSTITUTE**

Gregersensvej 1
DK-2630 Taastrup
+45 72 20 20 00
info@teknologisk.dk
www.teknologisk.dk

Page 1 of 6
Init.: CHF/LELN
Order no.: 981419
Encl.: 0

Assignor: Kvadrat A/S, Lundbergsvej 10, DK-8400 Ebeltøft

Material: Sample of upholstery fabric designated: Sabi. See page 2 for detailed sample description.

Sampling: The assignor confirms having selected the product. The product was forwarded by the assignor and received at Danish Technological Institute on 21 May 2021.

Period: The test took place from 21 May 2021 to 21 June 2021.

Method: The test methods used are referenced in connection with the results. See page 6.

Test results: The results are shown on page 6.

Terms: This test was conducted accredited in accordance with international requirements (ISO/IEC 17025:2017) and in accordance with the General Terms and Conditions of Danish Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent.

Place: Danish Technological Institute, Taastrup, Environmental Technology

Signature: This document is only valid with a digital signature from Danish Technological Institute. The date of issue appears from the digital signature.

Charlotte Fischer
Senior Consultant



DIGITALLY SIGNED DOCUMENT

8 October 2021

DANISH TECHNOLOGICAL INSTITUTE








DANAK

TEST Reg.no. 2



Samples

Sample mark	Description	Photo
121	Sample of upholstery fabric Designated: Sabi Fibre content: 65% new wool, 23% recycled wool, 12% nylon, worsted	
151	Sample of upholstery fabric Designated: TR 2131/ Recycled wool	
171	Sample of upholstery fabric Designated: TR 2131/ Recycled wool	
181	Sample of upholstery fabric Designated: TR 2131/ Recycled wool	
191	Sample of upholstery fabric Designated: TR 2131/ Recycled wool	








Samples (*continued*)

Sample mark	Description	Photo
221	Sample of upholstery fabric Designated: TR 2131/ Recycled wool	
291	Sample of upholstery fabric Designated: TR 2131/ Recycled wool	
351	Sample of upholstery fabric Designated: TR 2131/ Recycled wool	
441	Sample of upholstery fabric Designated: TR 2131/ Recycled wool	
551	Sample of upholstery fabric Designated: TR 2131/ Recycled wool	








Samples (*continued*)

Sample mark	Description	Photo
581	Sample of upholstery fabric Designated: TR 2131/ Recycled wool	
631	Sample of upholstery fabric Designated: TR 2131/ Recycled wool	
661	Sample of upholstery fabric Designated: TR 2131/ Recycled wool	
721	Sample of upholstery fabric Designated: TR 2131/ Recycled wool	
741	Sample of upholstery fabric Designated: TR 2131/ Recycled wool	



Samples (*continued*)

Sample mark	Description	Photo
771	Sample of upholstery fabric Designated: TR 2131/ Recycled wool	
791	Sample of upholstery fabric Designated: TR 2131/ Recycled wool	
851	Sample of upholstery fabric Designated: TR 2131/ Recycled wool	
921	Sample of Upholstery fabric Designated TR 1231 recycled wool/Sabi	
971	Sample of Upholstery fabric Designated TR 1231 recycled wool/Sabi	



Results

Test of Sample of upholstery fabric designated: Sabi

Colour fastness to artificial light: Xenon arc fading lamp test

EN ISO 105-B02:2014 Method 2

1-8 scale, 8 best rating

Test apparatus: Atlas Ci4000 Xenon Weather-Ometer

Sample mark	Colour fastness
121	5-6
151	5-6
171	5
181	5-6
191	5-6
221	5-6
291	5
351	5-6
441	6
551	6
581	5-6
631	6-7
661	5
721	6
741	5
771	5-6
791	5
851	4
921	6-7
971	5
