

Test Report

Report Number:
103975-1-TEX



**DANISH
TECHNOLOGICAL
INSTITUTE**

Gregersensvej 1
DK-2630 Taastrup
+45 72 20 20 00
info@teknologisk.dk
www.teknologisk.dk

Page 1 of 4
Init.: CHF/LELN
Order no.: 103975
Encl.: 0

Assignor: Febrik B.V., Minosstraat 20, NL-5048 CK Tilburg, Netherlands

Material: Sample of upholstery fabric designated: MIZMAZE. See page 2 for detailed sample description.

Sampling: The assignor confirms having selected the product. The product was forwarded by the assignor and received at Danish Technological Institute on 18 October 2021.

Period: The test took place from 19 October 2021 to 28 October 2021.

Method: The test methods used are referenced in connection with the results. See page 4.

Test results: The results are shown on page 4.

Terms: This test was conducted accredited in accordance with international requirements (ISO/IEC 17025:2017) and in accordance with the General Terms and Conditions of Danish Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent.

Place: Danish Technological Institute, Taastrup, Environmental Technology

Signature: This document is only valid with a digital signature from Danish Technological Institute. The date of issue appears from the digital signature.

Charlotte Fischer
Senior Consultant



DIGITALLY SIGNED DOCUMENT

28 October 2021

DANISH TECHNOLOGICAL INSTITUTE





DANAK

TEST Reg.no. 2









Samples

Sample mark	Description	Photo
122	Sample of upholstery fabric Designated: MIZMAZE	
212	Sample of upholstery fabric Designated: MIZMAZE	
252	Sample of upholstery fabric Designated: MIZMAZE	
342	Sample of upholstery fabric Designated: MIZMAZE	
392	Sample of upholstery fabric Designated: MIZMAZE	
562	Sample of upholstery fabric Designated: MIZMAZE	



Samples (*continued*)

Sample mark	Description	Photo
322	Sample of upholstery fabric Designated: MIZMAZE	
682	Sample of upholstery fabric Designated: MIZMAZE	
712	Sample of upholstery fabric Designated: MIZMAZE	
762	Sample of upholstery fabric Designated: MIZMAZE	
882	Sample of upholstery fabric Designated: MIZMAZE	
962	Sample of upholstery fabric Designated: MIZMAZE	



Results

Test of Sample of upholstery fabric designated: MIZMAZE

Colour fastness to rubbing

EN ISO 105-X12:2016
1-5 scale, 5 best rating

Test conditions: 21°C, 65% RH
Rubbing finger: Cylinder 16 mm

Force: 9 N

Staining	Warp direction		Weft direction	
	Dry rubbing	Wet rubbing	Dry rubbing	Wet rubbing
122	4-5	4-5	4-5	4-5
212	4-5	4-5	4-5	4-5
252	4	4-5	4	4-5
342	4	4	4-5	4-5
392	4	4	4	4
562	4	4	4	4
322	4-5	4-5	4-5	4-5
682	4	4-5	4	4-5
712	4-5	4-5	4-5	4-5
762	4-5	4-5	4-5	4-5
882	4-5	4-5	4-5	4-5
962	4	4-5	4	4-5
