

Test Report

Report Number:
108178-11-TEX



**DANISH
TECHNOLOGICAL
INSTITUTE**

Gregersensvej 1
DK-2630 Taastrup
+45 72 20 20 00
info@teknologisk.dk
www.teknologisk.dk

Page 1 of 4
Init.: CHF/LELN
Order no.: 108178
Encl.: 0

Assignor: Kinnasand GmbH, Danziger Strasse 6 , D-26655 Westerstede, Germany

Material: Sample of curtain fabric designated: Aerio. See page 2 for detailed sample description.

Sampling: The assignor confirms having selected the product. The product was forwarded by the assignor and received at Danish Technological Institute on 9 November 2021.

Period: The test took place from 10 November 2021 to 7 December 2021.

Method: The test methods used are referenced in connection with the results. See page 4.

Test results: The results are shown on page 4.

Terms: This test was conducted accredited in accordance with international requirements (ISO/IEC 17025:2017) and in accordance with the General Terms and Conditions of Danish Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent.

Place: Danish Technological Institute, Taastrup, Environmental Technology

Signature: This document is only valid with a digital signature from Danish Technological Institute. The date of issue appears from the digital signature.

Charlotte Fischer
Senior Consultant



DIGITALLY SIGNED DOCUMENT

8 December 2021

DANISH TECHNOLOGICAL INSTITUTE





DANAK

TEST Reg.no. 2




Samples

Sample mark	Description	Photo
Col. 0002	Sample of curtain fabric Designated: Aerio	
Col. 0006	Sample of curtain fabric Designated: Aerio	
Col. 0010	Sample of curtain fabric Designated: Aerio	
Col. 0014	Sample of curtain fabric Designated: Aerio	
Col. 0034	Sample of curtain fabric Designated: Aerio	



Samples (*continued*)

Sample mark	Description	Photo
Col. 0013	Sample of curtain fabric Designated: Aerio	
Col. 0012	Sample of curtain fabric Designated: Aerio	
Col. 0016	Sample of curtain fabric Designated: Aerio	
Col. 0024	Sample of curtain fabric Designated: Aerio	



Results

Test of Sample of curtain fabric designated: Aerio

Colour fastness to artificial light: Xenon arc fading lamp test

EN ISO 105-B02:2014 Method 2

1-8 scale, 8 best rating

Test apparatus: Atlas Ci4000 Xenon Weather-Ometer

Sample mark	Colour fastness
Col. 0002	7
Col. 0006	6-7
Col. 0010	6-7
Col. 0014	7
Col. 0034	6-7
Col. 0013	7
Col. 0012	6-7
Col. 0016	6-7
Col. 0024	6-7
