



**Test report Textile Pilling
NS-EN ISO 12945-2 :2000**

Client SAHCO GmbH KREUZBURGER STRASSE 17-19 DE-9047 1 NÜRNBERG Tyskland		Product Nympha	
Client's reference Sarah Kemmerer		Product specification - tested object	
Date 31.05.2021		Date of receipt, tested object 27.05.2021	R-no. R16901
		Test completed date 28.05.2021	Rev. no. / Rev. date 0/

Manufacturer:

Composition: 100% cotton

Loading Mass : 415 g Type felt: Woven

The samples are conditioned at 20 degrees C and 65 % relative humidity for 18 hours

Numerical assessment of pilling is done on a Martindale abrasion tester according to NS-EN ISO 12945-2. The samples are given a multi-directional movement and rubbed against fabric of 100% wool (SM 25). Three samples are used and they are examined at 500, 1000, 2000 and 5000 rubs. The average on each stage is reported as the pilling grade.

The samples are examined on a scale from 1-5 where 5 is best. Examined by 1 person.

Results:	500 Cycles:	3-4
	1000 Cycles:	3-4
	2000 Cycles:	3-4
	5000 Cycles:	3-4

Comments:

Deviations from test standards:

Bård Vestre
Manager