

Investigation report

SAHCO GmbH
Frau Sarah Kemmerer
Kreuzburger Str. 17-19

DE 90471.Nürnberg

contact Detlef v. Seyfried
department Laboratory\Laboratory Manager
phone +49 (0) 5206 / 91 07 -57
fax +49 (0) 5206 / 91 07 -34
e-mail detlef.vonSeyfried@delcotex.de
date 04.11.2021

investigation report No. 21/4020

order description: Textiles - Tests for colour fastness - Part B02: Colour fastness to artificial light: Xenon arc fading lamp test DIN EN ISO 105-B02 (2014-11) method 2

test samples: "Art. Ecriture in diversen Farben"

sampling: by the client

orderer: see address

date of order: 18.10.2021

receipt of order: 19.10.2021

date of testing: 02.11.2021

Remark: The results are valid only for the tested object. The accreditation applies for the methods listed in the annex to the certificate D-PL-17323-01-00. Accredited test methods are underlined. The valuations and Interpretations in the investigation report are not subject to accreditation. Tests conducted through co-operation partners are marked with °. All information provided by the customer, which is taken over unchecked and thus reflected in the examination report, are placed in quotation marks on the first page of the investigation report. The content of this investigation report will not be passed to third persons without written approval of the orderer. The partial publication of the test report, as well as the usage for commercial process, is only allowed with a permission of the DELCOTEX Delius Techtex GmbH & Co. KG. Remnants of test material will be destroyed after 3 months. Previously stated specifications / data sheets / certificates are only characters and no warranties. Also no warranty in case of durability will be overtaken. Finally our general delivery and payment conditions are valid (please see www.textillabor.eu).

Investigation report No. 21/4020

instructions for performing

method: Textiles - Tests for colour fastness - Part B02: Colour fastness to artificial light: Xenon arc fading lamp test DIN EN ISO 105-B02 (2014-11) method 2

measuring conditions:

tester Atlas Xenotest alpha LM

light xenon arc beam

filtersystem type 7

sample movement interchangeable barrel

exposure time 180 h - to note 6

test equipment number: PM-Nr. 887001

test results

"Art. Ecriture in diversen Farben"

article / colour	Note*
Ecriture 0100	›6
Ecriture 0130	›6
Ecriture 0150	›6
Ecriture 0170	›6
Ecriture 0180	6
Ecriture 0200	6
Ecriture 0210	6
Ecriture 0240	5-6
Ecriture 0270	5
Ecriture 0380	6
Ecriture 0410	6
Ecriture 0470	›6
Ecriture 0570	6
Ecriture 0580	6
Ecriture 0640	›6
Ecriture 0710	6
Ecriture 0760	›6
Ecriture 0780	6
Ecriture 0910	6
Ecriture 0970	5-6

* The results based on using the blue scale. Note 1 = intense colour change Note 8 = no colour change


 i.A. Detlef v. Seyfried

Laboratory/Laboratory manager

DELCOTEX Delius Techtex GmbH & Co. KG

Only the information in the signed test report is considered as binding.

Investigation report No. 21/4020

Attachment

article:

"Art. Ecriture in diversen Farben"

method:

Textiles - Tests for colour fastness - Part B02: Colour fastness to artificial light: Xenon arc fading lamp test DIN EN ISO 105-B02 (2014-11) method 2



Investigation report No. 21/4020

Attachment

article: "Art. Ecriture in diversen Farben"

method: Textiles - Tests for colour fastness - Part B02: Colour fastness to artificial light: Xenon arc fading lamp test DIN EN ISO 105-B02 (2014-11) method 2

