

Investigation report

SAHCO GmbH
Frau Sarah Kemmerer

Kreuzburger Str. 17-19

DE 90471 Nürnberg

contact Detlef v. Seyfried
department Laboratory\Laboratory Manager
phone +49 (0) 5206 / 91 07 -57
fax +49 (0) 5206 / 91 07 -34
e-mail detlef.vonSeyfried@delcotex.de
date 11.11.2021

investigation report No. 21/4019

order description: Textiles - Tests for colour fastness - Part B02: Colour fastness to artificial light: Xenon arc fading lamp test DIN EN ISO 105-B02 (2014-11) method 2
test samples: "Art. Clifford in diversen Farben"
sampling: by the client
orderer: see address
date of order: 18.10.2021
receipt of order: 19.10.2021
date of testing: 11.11.2021

Remark: The results are valid only for the tested object. The accreditation applies for the methods listed in the annex to the certificate D-PL-17323-01-00. Accredited test methods are underlined. The valuations and Interpretations in the investigation report are not subject to accreditation. Tests conducted through co-operation partners are marked with °. All information provided by the customer, which is taken over unchecked and thus reflected in the examination report, are placed in quotation marks on the first page of the investigation report. The content of this investigation report will not be passed to third persons without written approval of the orderer. The partial publication of the test report, as well as the usage for commercial process, is only allowed with a permission of the DELCOTEX Delius Techtex GmbH & Co. KG. Remnants of test material will be destroyed after 3 months. Previously stated specifications / data sheets / certificates are only characters and no warranties. Also no warranty in case of durability will be overtaken. Finally our general delivery and payment conditions are valid (please see www.textillabor.eu).

Investigation report No. 21/4019

instructions for performing

method: Textiles - Tests for colour fastness - Part B02: Colour fastness to artificial light: Xenon arc fading lamp test DIN EN ISO 105-B02 (2014-11) method 2

measuring conditions:

tester Atlas Xenotest alpha LM
 light xenon arc beam
 filtersystem type 7
 sample movement interchangeable barrel
 exposure time 180 h - to note 6
 test equipment number: PM-Nr. 887001

test results

"Art. Clifford in diversen Farben"

article / colour	Note*
Clifford 0120	5-6
Clifford 0150	6
Clifford 0230	5
Clifford 0370	5
Clifford 0560	5-6
Clifford 0940	6

* The results based on using the blue scale. Note 1 = intense colour change Note 8 = no colour change



i.A. Detlef v. Seyfried

Laboratory/Laboratory manager

DELCOTEX Delius Techtex GmbH & Co. KG

Only the information in the signed test report is considered as binding.

Investigation report No. 21/4019

Attachment

article: "Art. Clifford in diversen Farben"

method: Textiles - Tests for colour fastness - Part B02: Colour fastness to artificial light: Xenon arc fading lamp test DIN EN ISO 105-B02 (2014-11) method 2

