



## TEST REPORT

**Client:** SAHCO UK  
 G24 Design Centre Chelsea Harbour  
 London  
 SW10 0XE

**Entry No:** 89782

**Date received:** 23/08/2017

**Client's Description:** Sample of fabric: Dalston 2760, Composition: 100% Polyester FR

**Test Required:** Flammability in accordance with The Furniture and Furnishings (Fire) (Safety) Regulations 1988 and Amendments Schedule 4 Part I and Schedule 5 Part I

**Pre-treatment:** None

**Conditioning:** A minimum of 96 hours at 50+/-20% Relative Humidity, 20+/-5°C

**Date Tests Completed:** 01/09/2017

**Method of Test:** BS 5852: Part 1: 1979

The following test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

Ignition Source	Observations	Result
0 (cigarette)	No flaming or progressive smouldering was observed within one hour of placement of the cigarettes.	PASS
1 (butane flame)	Flaming ceased within the specified two minute period after removal of the butane flame and no progressive smouldering occurred.	PASS

**Note:** A 20-22 kg/m<sup>3</sup> non fire retardant polyurethane foam was used as the filling for the cigarette tests.

### Comments

On the basis of the tests carried out this sample of fabric meets the requirements of Schedule 4 Part I and also meets Schedule 5 Part I.

-----End of Document-----

*This is hereby certified to be a correct return of the tests made of the items referred to herein*



Giles Dive  
 Technician  
 4 September 2017

- ❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days.
  - ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
  - ❖ Uncertainty budgets for test methods contained within this report are available on request.
- This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.

