

Investigation report

SAHCO GmbH Fr. Sarah Kemmerer

Kreuzburger Str. 17-19

DE 90471 Nürnberg

contact	Erik Radl
department	Laboratory\Laboratory
phone	+49 (0) 5206 / 91 07 -52
fax	+49 (0) 5206 / 91 07 -34
e-mail	erik.radl@delcotex.de
date	21.01.2022

investigation report No. 21/4780

order description:	<u>Textiles - Tests for colour fastness - Part B02: Colour fastness to artificial light: Xenon arc fading lamp test DIN EN ISO 105-B02 (2014-11) method 2</u>
test samples:	"Art. Corallium/600742 in diversen Farben"
sampling:	by the client
orderer:	see address
date of order:	09.12.2021
receipt of order:	10.01.2022
date of testing:	21.01.2022

Remark: The results are valid only for the tested object. Accredited test methods are underlined. The accreditation applies for the methods listed in the annex to the certificate D-PL-17323-01-00. The valuations and Interpretations in the investigation report are not subject to accreditation. Tests conducted through co-operation partners are marked with °. All information provided by the customer, which is taken over unchecked and thus reflected in the examination report, are placed in quotation marks on the first page of the investigation report. Changes to the original investigation report are marked with a vertical line in the left margin and a revision level is added to the investigation report number. The content of this investigation report will not be passed to third persons without written approval of the orderer. The partial publication of the test report, as well as the usage for commercial process, is only allowed with a permission of the DELCOTEX Delius Techtex GmbH & Co. KG. Remnants of test material will be destroyed after 3 months. Previously stated specifications / data sheets / certificates are only characters and no warranties. Also no warranty in case of durability will be overtaken. Finally our general delivery and payment conditions are valid (please see www.textillabor.eu).

Investigation report No. 21/4780

instructions for performing

method: Textiles - Tests for colour fastness - Part B02: Colour fastness to artificial light: Xenon arc fading lamp test DIN EN ISO 105-B02 (2014-11) method 2

measuring conditions:

tester Atlas Xenotest alpha LM
light xenon arc beam
filtersystem type 7
sample movement interchangeable barrel
exposure time 275 h - to note 6
test equipment number: PM-Nr. 887003

test results


"Art. Corallium/600742 in diversen Farben"

article / colour	Note*
Corallium 0100	>6
Corallium 0150	>6
Corallium 0410	>6
Corallium 0730	>6
Corallium 0790	>6
Corallium 0940	6

* The results based on using the blue scale.

Note 1 = intense colour change

Note 8 = no colour change



i.A. Erik Radl

Laboratory/Laboratory

DELCOTEX Delius Techtex GmbH & Co. KG

Only the information in the signed test report is considered as binding.

Investigation report No. 21/4780

Attachment

article:

"Art. Corallium/600742 in diversen Farben"

method:

Textiles - Tests for colour fastness - Part B02: Colour fastness to artificial light: Xenon arc fading lamp test DIN EN ISO 105-B02 (2014-11) method 2

Corallium 0100

Corallium 0150

Corallium 0410

Corallium 0730

Corallium 0790

Corallium 0940

