### **Test Report**

Report Number: 119466-1-TEX



#### DANISH TECHNOLOGICAL

INSTITUTE

Gregersensvej 1 DK-2630 Taastrup +45 72 20 20 00 info@teknologisk.dk www.teknologisk.dk

Page 1 of 5 Init.: CHF/LELN Order no.: 119466

nder no.: 119466 Encl.: 0

Assignor: Kvadrat A/S, Lundbergsvej 10, DK-8400 Ebeltoft

**Material:** Samples of upholstery fabric designated: Clay. See page 2 for detailed sample description.

Sampling: The assignor confirms having selected the product. The product was forwarded by the

assignor and received at Danish Technological Institute on 19 January 2022.

Period: The test took place from 20 January 2022 to 11 February 2022.

**Method:** The test methods used are referenced in connection with the results. See page 5.

**Test results:** The results are shown on page 5.

Terms: This test was conducted accredited in accordance with international requirements (ISO/IEC

17025:2017) and in accordance with the General Terms and Conditions of Danish

Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent.

Place: Danish Technological Institute, Taastrup, Environmental Technology

Signature: This document is only valid with a digital signature from Danish Technological Institute. The

date of issue appears from the digital signature.

Charlotte Fischer Senior Consultant



DANISH TECHNOLOGICAL INSTITUTE







# Samples

| Sample mark | Description   | Photo           |  |
|-------------|---|-----------------|--|
| 1           | Sample of upholstery fabric Designated: Clay Fibre content: 76% linen, 21% cotton, 3% polyester |                 |  |
| 2           | Sample of upholstery fabric Designated: Clay Fibre content: 76% linen, 21% cotton, 3% polyester | esignated: Clay |  |
| 3           | Sample of upholstery fabric Designated: Clay Fibre content: 76% linen, 21% cotton, 3% polyester |                 |  |
| 4           | Sample of upholstery fabric Designated: Clay Fibre content: 76% linen, 21% cotton, 3% polyester |                 |  |
| 5           | Sample of upholstery fabric Designated: Clay Fibre content: 76% linen, 21% cotton, 3% polyester |                 |  |
| 6           | Sample of upholstery fabric Designated: Clay Fibre content: 76% linen, 21% cotton, 3% polyester |                 |  |

119466-1-TEX Page 2 of 5



# Samples (continued)

| Sample mark | Description   | Photo |
|-------------|---|-------|
| 7           | Sample of upholstery fabric Designated: Clay Fibre content: 76% linen, 21% cotton, 3% polyester |       |
| 8           | Sample of upholstery fabric Designated: Clay Fibre content: 76% linen, 21% cotton, 3% polyester |       |
| 9           | Sample of upholstery fabric Designated: Clay Fibre content: 76% linen, 21% cotton, 3% polyester |       |
| 10          | Sample of upholstery fabric Designated: Clay Fibre content: 76% linen, 21% cotton, 3% polyester |       |
| 11          | Sample of upholstery fabric Designated: Clay Fibre content: 76% linen, 21% cotton, 3% polyester |       |
| 12          | Sample of upholstery fabric Designated: Clay Fibre content: 76% linen, 21% cotton, 3% polyester |       |

119466-1-TEX Page 3 of 5



# Samples (continued)

| Sample mark | Description   | Photo |
|-------------|---|-------|
| 13          | Sample of upholstery fabric Designated: Clay Fibre content: 76% linen, 21% cotton, 3% polyester |       |
| 14          | Sample of upholstery fabric Designated: Clay Fibre content: 76% linen, 21% cotton, 3% polyester |       |
| 15          | Sample of upholstery fabric Designated: Clay Fibre content: 76% linen, 21% cotton, 3% polyester |       |
| 16          | Sample of upholstery fabric Designated: Clay Fibre content: 76% linen, 21% cotton, 3% polyester |       |
| 17          | Sample of upholstery fabric Designated: Clay Fibre content: 76% linen, 21% cotton, 3% polyester |       |

119466-1-TEX Page 4 of 5



#### Results

#### Test of Samples of upholstery fabric designated: Clay

#### Colour fastness to artificial light: Xenon arc fading lamp test

EN ISO 105-B02:2014 Method 2

1-8 scale, 8 best rating

Test apparatus: Atlas Ci4000 Xenon Weather-Ometer

| Sample mark | Colour fastness |  |
|-------------|-----------------|--|
| 1           | 5-6             |  |
| 2           | 5               |  |
| 3           | 5-6             |  |
| 4           | 5-6             |  |
| 5           | 5-6             |  |
| 6           | 5               |  |
| 7           | 5               |  |
| 8           | 5-6             |  |
| 9           | 5-6             |  |
| 10          | 5-6             |  |
| 11          | 5               |  |
| 12          | 4               |  |
| 13          | 5               |  |
| 14          | 5-6             |  |
| 15          | 5               |  |
| 16          | 5-6             |  |
| 17          | 5               |  |

119466-1-TEX Page 5 of 5