

EN 29053 - Determination of airflow resistance

Direct airflow method - method A


Client Kvadrat

Date: 15-06-20

Fabric details Type: Reflect
Colour: 204
Order:
Pick:
Manufacturer: Kvadrat

Specimen Diameter: 100 mm
Thickness: 0.47 mm
Area specific mass: 306 g/m²

u_l (mm/s)	$R_{s,l}$ (Pa s/m)
16.53	2511
14.16	2507
11.80	2500
9.44	2497
7.12	2480
4.80	2438



Airflow Resistance

$R_s = 2430$ Pa s/m