

Müller-BBM GmbH
Robert-Koch-Str. 11
82152 Planegg bei München

Telephone +49(89)85602 0
Telefax +49(89)85602 111

www.MuellerBBM.de

M. Eng. Philipp Meistring
Telephone +49(89)85602 228
Philipp.Meistring@mbbm.com

2020-06-17
M100827/222 Version 1 MSG/STEG

Curtain fabric Ria by Kvadrat A/S

**Determination of airflow resistance
according to DIN EN ISO 9053-1**

Test Report No. M100827/222

Client:	Kvadrat A/S Lundbergsvej 10 8400 Ebeltoft DENMARK
Consultant:	M. Eng. Philipp Meistring M.Sc. Paul Siegmüller
Report date:	2020-06-17
Delivery date of test object:	2020-06-05
Date of test:	2020-06-10
Total number of pages:	In total 7 pages, thereof 4 pages text, 1 page Appendix A and 2 pages Appendix B.

Müller-BBM GmbH
HRB Munich 86143
VAT Reg. No. DE812167190

Managing directors:
Joachim Bittner, Walter Grotz,
Dr. Carl-Christian Hantschk,
Dr. Alexander Ropertz,
Stefan Schierer, Elmar Schröder

Table of contents

1	Task	3
2	Basis	3
3	Test object	3
4	Execution of measurements	3
5	Measurement results	4
6	Remarks	4

Appendix A: Measurement results and evaluation

Appendix B: Description of the test procedure and list of test equipment

1 Task

On behalf of Kvadrat A/S, 8400 Ebeltoft, Denmark, the airflow resistance of the fabric type Ria was to be determined according to DIN EN ISO 9053-1 [1].

2 Basis

This test report is based on the following document:

- [1] DIN EN ISO 9053-1: Acoustics –Determination of airflow resistance – Part 1: Static airflow method (ISO 9053-1:2018); German version EN ISO 9053-1:2018. March 2019

3 Test object

The tested fabric is described in Table 1. The indicated characteristic values were determined by the testing laboratory on the basis of the sample delivered by the manufacturer.

Table 1. Test object.

Test object (information provided by the client)	Area specific mass m' [g/m ²]	Thickness t [mm]
Fabric type Ria by Raf Simons, color 541 manufacturer Kvadrat A/S, material 84 % new wool worsted 12 % viscose, 4 % nylon	593	2.04

4 Execution of measurements

The airflow resistance was determined according to DIN EN ISO 9053-1 [1].

The test method, the test facility and the test equipment used are described in Appendix B.

5 Measurement results


For the tested fabric the following specific airflow resistance was determined:

- fabric type Ria $R_s = 482 \text{ Pa} \cdot \text{s/m}$

The measurement results are shown in the diagram and table in the test certificate in Appendix A of this report.

6 Remarks

The test results exclusively relate to the investigated subjects and conditions described.



M.Eng. Philipp Meistring
(Project manager)



M. Sc. Paul Siegmüller
(Responsible)

This test report may only be published, shown or copied as a whole, including its appendices. The publishing of excerpts is only possible with prior consent of Müller-BBM.



Testing laboratory accredited by DAkkS according to DIN EN ISO/IEC 17025:2018.
The accreditation is valid only for the scope listed in the annex of the accreditation certificate.

ISO 9053-1
Determination of airflow resistance

Client: Kvadrat A/S
Lundbergsvej 10
8400 Ebeltoft
Denmark

Project number: M100827

Sample number: 13901

Test object: - fabric: Ria by Raf Simons color 541
- material: 84% new wool, worsted / 12% viscose / 4% nylon


Diameter: 100 mm
Thickness: 2.04 mm
Area-specific mass: 593 g/m²

Barometric pressure:
 $B = 94,7 \text{ kPa}$

Temperature:
 $\theta = 24,0 \text{ }^\circ\text{C}$

Relative humidity:
 $r. h. = 24,5 \%$

$u/$ (mm/s)	$R_s/$ (Pa s/m)
0.49	486
1.95	488
3.40	479
4.85	480
6.31	483
7.76	485
9.21	488
10.67	489
12.12	487
13.58	492



Specific airflow resistance $R_s = 482 \text{ Pa s/m}$

MÜLLER-BBM

Laboratory: Planegg
Responsible: Siegmüller
Date: 2020-06-10

\\S-muc-fs01\allefirmen\MP\Proj\100\W100827\M100827_222_Pbe_1E.DOCX : 18.06.2020

m\ans 1,14,7256,28813 - s\MP\Proj\100\W100827\Mans\Data\20200610\Ria_541.mns (18.06.2020)

Description of the test procedure for the determination of the airflow resistance

1 Measurand

The specific airflow resistance R_S of the test object was determined. For this purpose the air pressure difference in front of as well as behind the test object was measured at different volumetric airflow rates. The specific airflow resistance $R_{S,i}$ for each volumetric airflow rate $q_{v,i}$ determined was calculated using the following equation:

$$R_{S,i} = \frac{\Delta p_i \cdot A}{q_{v,i}}$$

With

$R_{S,i}$ specific airflow resistance in Pa s/m;

Δp_i air pressure difference across the test object with respected to the atmosphere in Pa;

A cross-sectional area of the test object perpendicular to the direction of flow in m²;

$q_{v,i}$ volumetric airflow rate passing through the test object in m³/s;

u_i linear airflow velocity in m/s;

In addition the linear airflow velocity u_i was determined:

$$u_i = \frac{q_{v,i}}{A}$$

The indicated measurement result is the specific airflow resistance R_S , which is calculated for an airflow velocity of $u = 0.0005$ m/s by extrapolation with help of the linear regression.

2 Test procedure

The direct airflow method (static airflow method according to DIN EN ISO 9053-1 [1]) was applied. A steady unidirectional airflow with different air flow rates is pressed through the test object in the specimen holder. The resulting pressure drop between the two free faces of the test object is measured.

The specimen holder had a diameter of $D = 100$ mm.

3 List of test equipment

The test equipment used is listed in Table B.1.

Table B.1. Test equipment

Name	Manufacturer	Type	Serial-No.	Calibration valid until
Measurement system airflow resistance	Müller-BBM	M89319-00	315003	2020-03
Software for measurement and evaluation	Müller-BBM Acoustic Solution	m ars	1.14.7256. 28813	
Digital measuring slide	Mitutoyo	CD-15PPR	07019377	2021-03
Electronic balance	Kern	KB1200-2N	W1402353	2021-03