



DANISH  
TECHNOLOGICAL  
INSTITUTE

### Test Report no. A 487026-3

Gregersensvej  
DK-2630 Taastrup  
Tel. +45 72 20 20 00  
Fax +45 72 20 20 19

info@teknologisk.dk  
www.teknologisk.dk

Kvadrat Holding A/S, Lundbergsvej 10, 8400 Ebeltøft	
Test material: Upholstery fabric Savanna	
Design:	Received: 17-07-2012 Completed: 27-08-2012
Fibre content: 34% polyester, 31% wool, 26% acrylic, 4% cotton, 3% polyamide, 2% linen (Manufacturer's information)	Sample no.: 487026-3
Care label: (Not given)	Your ref.: Lone Henriksen

Test Methods	Results
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	672 Colour fastness: 7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	622 Colour fastness: 7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	442 Colour fastness: 7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	292 Colour fastness: 6-7

## Test Report no. A 487026-3

Test Methods	Results
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	242 Colour fastness: 6-7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	952 Colour fastness: 6-7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	202 Colour fastness: 6-7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	222 Colour fastness: 6
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	262 Colour fastness: 6-7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	192 Colour fastness: 6-7

## Test Report no. A 487026-3

Test Methods	Results
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	152 Colour fastness: 6-7
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	122 Colour fastness: 6-7

The test has been performed according to the attached conditions, which are according to the guidelines laid down by DANAK (The Danish Accreditation). The testing is only valid for the tested specimen. The test report may only be extracted, if the laboratory has approved the extract.

This report was generated by software version 2.43 of 2011-03-21.

27 August 2012, Danish Technological Institute, Textile



Charlotte Fischer  
 Ph. Direct: +45 72 20 21 35  
 E-mail: charlotte.fischer@teknologisk.dk

Test responsible



Jeanette Berner Hansen  
 Ph. Direct: +45 72 20 21 39  
 E-mail: jeanette.berner.hansen@teknologisk.dk

Co-reader