

Müller-BBM GmbH
Robert-Koch-Strasse 11
82152 Planegg
Germany

Tel. +49 (89) 85602-0
Fax +49 (89) 85602-111

www.MuellerBBM.de

M. Eng. Philipp Meistring
Tel. +49 (89) 85602-228
Philipp.Meistring@MuellerBBM.de

2009-07-13
M60 836/50 msg/jre

Ginger Manufacturer Kvadrat A/S

**Determination of the
air flow resistance according to EN 29053**

Test Report No. M60 836/50

Client:	Kvadrat A/S Lundbergsvej 10 DK – 8400 Ebeltoft
Acoustic consultant:	M. Eng. Philipp Meistring
Date of report:	2009-07-13
Date of delivery of test objects:	2009-07-09
Date of measurements:	2009-07-09
Total number of pages:	In total 6 pages: 4 pages text, 1 page Appendix A and 1 page Appendix B

Table of contents

1	Task	3
2	Basics	3
3	Test object	3
4	Execution of measurements	3
5	Measurement results	4
6	Remark	4
	Appendix A: Measurement results and evaluation	1
	Appendix B: List of test equipment	1

1 Task

On behalf of the Kvadrat A/S company, DK – 8400 Ebeltoft, the airflow resistance of the curtain fabric Ginger has to be measured according to EN 29053 [1].

2 Basics

This test report is based on the following documents:

- [1] EN 29053 “Acoustics – Materials for acoustical applications – Determination of airflow resistance”. 1993

3 Test object

The tested material is described by the manufacturer as follows:

- curtain fabric
- manufacturer Kvadrat A/S
- type Ginger
- material 100 % Trevira CS

Müller-BBM has determined the following parameters:

- area specific mass $m'' = 261 \text{ g/m}^2$
- total thickness $t = 0.59 \text{ mm}$

4 Execution of measurements

The airflow resistance was determined according to EN 29053 [1] .

The measurements for the determination of the airflow resistance were carried out at different air velocities. The continuous airflow method was applied. The measurement cell (specimen holder) has a diameter of 100 mm. The test specimen was fitted flat over the measurement cell, without stretching the material, sealed at the edges and fixed.

According to the standard the specific airflow resistance R_s is indicated as measurement result which was determined by extrapolation (linear regression) at an airflow velocity of $u = 0.0005 \text{ m/s}$.

The test equipment listed in appendix B was used for the measurements.

5 Measurement results

For the tested fabric, type Ginger, a specific airflow resistance of $R_s = 33 \text{ Pa} \cdot \text{s/m}$ was determined.

For further information regarding the measurements, see Appendix A.

6 Remark

The determined test results only refer to the prevailing conditions on the day of measurements.

This test report may only be published and copied as a whole including all of its appendixes. The publishing of extracts requires the prior written consent of Müller-BBM GmbH.



Dr.-Ing. Andreas Meier



M. Eng. Philipp Meistring

MÜLLER-BBM

Accredited Test Laboratory
according to ISO/IEC 17025



DAP-PL-2465.10

DIN EN 29053


Bestimmung des Strömungswiderstandes

Auftraggeber: Kvadrat A/S, Lundsbergsvej 10, 8400 Ebeltoft Denmark
Auftragsnummer: M60836
Auftragsdatum: 09.07.2009

Dicke: 0,59 mm
Flächenbez. Masse: 261 g/m²
Dichte: 442,37 kg/m³
Prüfobjekt: - fabric Kvadrat A/S, type Ginger
 - material: 100 % Trevira CS

Probendurchmesser:
 $D = 100,0$ mm
 Luftdruck:
 $B = 95,5$ kPa
 Temperatur:
 $\theta = 25,5$ °C
 Relative Feuchte:
 $r. h. = 42,0$ %

v [mm/s]	R [Pa s/m]
5,90	34
8,56	34
9,45	34
10,33	34
11,22	34
12,11	35
12,99	34
13,88	34
14,77	35



Spezifischer Strömungswiderstand $R_s = 33$ Pa s/m

Prüfstelle: Müller-BBM Planegg
 Prüfer: Moll
 Prüfdatum: 09.07.2009

List of test equipment

For the measurements and evaluations, the following test equipment was applied:

Name	Manufacturer	Type	Serial-No.
Digital Mass Flow Controller	Bronkhorst	E-201CV-5KO-RGD-33V	M8211608A
Digital Power Supply / Readout Systems	Bronkhorst	E-7100-13-01-01-RBB	M8211608B
Differential pressure transmitter with DSCM-A	Halstrup Walcher	P26	M8211704G
Software for data logging and evaluation	Müller-BBM	AirFlowControl	v1.1