SGS

Tested For:

Lone Henriksen

Phone:

011 45 89 53 18 60

lh@kvadrat.dk

Received:

8/9/2021

Kvadrat A/S

Fax:

Completed:

8/13/2021

Lundbergsvej 10 DK-8400 Ebeltoft

Mobile:

Code:

U

PO#: Emall: **Test Report:**

3-44745-0

Denmark

Key Test:

CAN/ULC-S109-14 Small Flame Test

226

Client's Identification:

Style: Waver. Content: 100% Trevira CS. Width: App. 118 inches. Finish: None. Weight Range: 16-340 g/m². Weight: 16 g/m²-1.52 oz/ly. End Use: Curtain.

Test Category: CAN/UL Small

LE 2014; V 7/21 DK

Specifier: CAN/UL

/rb /dv

TEST PERFORMED: CAN/ULC-S109-14 * - Standard for Flame Tests of Flame-Resistant Fabrics & Films, Small Flame Test

(* Note: This document was prepared and published by Underwriters' Laboratories of Canada and is approved as a National Standard of Canada.)

PRECONDITIONING:

\boxtimes	Standard	method:	0.5	hour	@	105	士	2°C
-------------	----------	---------	-----	------	---	-----	---	-----

☐ Alternate method for materials that are affected by heating to 105°C:

☐ Desiccator method: 12 hours minimum @ 20 ± 2°C and 50 ± 5% RH

☐ Alternate oven method: 1 hour @ 60 ± 2°C

APPROXIMATE AREA DENSITY OF MATERIAL (as measured by SGS North America): 43.5 g/m²

CONVERSION FACTORS:

mm \div 25.4 = inches

 $g/m^2 \div 28.35 \times 0.0835 = oz/yd^2$

RESULTS ARE REPORTED:

☑ Initially
 ☐ After 10 dry cleanings
 ☐ After 10 launderings
 ☐ After 72 hours water leaching
 ☐ After 72 hours water leaching

☐ After scrubbing [code 630]

☐ After 360 hours accelerated weathering

[code 5518]

BG

Ver. 2021-03-09 10:35

Page 1 of 3

The results contained in this report relate only to the item(s) tested. The test report shall not be reproduced except in full, without written approval from SGS North America.



Lone Henriksen

Phone: Fax:

011 45 89 53 18 60

lh@kvadrat.dk

Received: Completed: 8/9/2021

Kvadrat A/S

Mobile:

Code:

8/13/2021

Lundbergsvej 10 DK-8400 Ebeltoft

PO#:

Emall:

3-44745-0

Test Report:

Denmark

Key Test:

CAN/ULC-S109-14 Small Flame Test

226

RESULTS:

Direction	Specimen #	Surface Flaming** (seconds)	Flaming Drip (seconds)	Damaged Length (mm)
	1	0	0	140
Length:	2	0	0	110
	3	0	0	130
	4	0	0	170
	5	0	0	135
			Average:	137
	6	0	0	155
	7	0	0	185
Width:	8	0	0	133
	9	0	0	155
	10	0	0	155
			Average:	157

REMARKS: None.

ACCEPTANCE CRITERIA:

	Surface Flaming (seconds)	Flaming Drip (seconds)	Damaged Length
Maximum Average:	ste ste	Not specified	165 mm (6.5")
Maximum Individual Specimen:	**	2.0	190 mm (7.5")

(** Surface Flaming values are required to be reported after removal of the 12 seconds igniting flame; however, these values are not required to be factored into determination of acceptance.)

BG

Ver. 2021-03-09 10:35

Page 2 of 3

The results contained in this report relate only to the item(s) tested. The test report shall not be reproduced except in full, without written approval from SGS North America.

Lone Henriksen Received: Tested For: Phone: 011 45 89 53 18 60 8/9/2021 Kvadrat A/S Fax: **Completed:** 8/13/2021 Lundbergsvej 10 DK-8400 Ebeltoft Mobile: Code: U PO#: **Test Report:** 3-44745-0 **Emall:** lh@kvadrat.dk Denmark **Key Test:** CAN/ULC-S109-14 Small Flame Test CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested: □ Complies: □ Does not comply CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above. AUG 2 6 2021 AUTHORIZED MATURE SGS NORTH AFFERICA Bobby Brown

BG

Ver. 2021-03-09 10:35

Page 3 of 3

226

The results contained in this report relate only to the item(s) tested. The test report shall not be reproduced except in full, without written approval from SGS North America.



Received: **Tested For: Lone Henriksen** Phone: 011 45 89 53 18 60 8/9/2021 Kvadrat A/S Fax: Completed: 8/16/2021 Lundbergsvei 10 DK-8400 Ebeltoft Mobile: Code: U1 P0#: **Test Report:** 3-44745-1 **Emall:** lh@kvadrat.dk Denmark **Key Test:** CAN/ULC S109-14 Large Flame Test Folded Specimen 457 **Client's Identification:** Style: Waver. Content: 100% Trevira CS. Width: App. 118 inches. Finish: None. Weight Range: 16-340g/m². Weight: 16 g/m²- 1.52 oz/ly. End Use: Curtain. Test Category: CAN/UL Large Folds LE: 2014; V 7/21 DK Specifier: CAN/UL /rb /dv TEST PERFORMED: CAN/ULC-S109-14 * - Standard for Flame Tests of Flame-Resistant Fabrics & Films, Large Flame Test, Folded Specimens (* Note: This document was prepared and published by Underwriters' Laboratories of Canada and is approved as a National Standard of Canada.) PRECONDITIONING: ☐ Standard method: 0.5 hour @ 105 ± 2°C ☑ Alternate method for materials that are affected by heating to 105°C: \boxtimes Desiccator method: 12 hours minimum @ 20 ± 2°C and 50 ± 5% RH ☐ Alternate oven method: 1 hour @ 60 ± 2°C APPROXIMATE AREA DENSITY OF MATERIAL (as measured by SGS North America): 43.5 g/m² **CONVERSION FACTORS:** $mm \div 25.4 = inches$ $g/m^2 \div 28.35 \times 0.0835 - oz/yd^2$

RESULTS ARE REPORTED:

[code 457] ☐ After 10 dry cleanings [code 688] ☐ After 10 launderings [code 630] ☐ After 72 hours water leaching [code 630] ☐ After scrubbing [code 861] ☐ After 360 hours accelerated weathering [code 6925]

JR

Ver. 2021-03-09 10:35

Page 1 of 2

The results contained in this report relate only to the item(s) tested. The test report shall not be reproduced except in full, without written approval from SGS North America.



Lone Henriksen

Phone:

011 45 89 53 18 60

Received:

8/9/2021

Kvadrat A/S

Fax:

Completed:

Test Report:

8/16/2021

Lundbergsvej 10 DK-8400 Ebeltoft

Mobile: P0#:

Code:

3-44745-1

U1

Email:

lh@kvadrat.dk

Denmark

Key Test:

CAN/ULC \$109-14 Large Flame Test Folded Specimen

457

RESULTS:

Direction	Specimen #	Surface Flaming** (seconds)	Flaming Drip (seconds)	Char Length (mm)
Longth	1	0	0	56
Length:	2	0	0	69
\\/idth	3	0	0	77
Width:	4	0	0	74

REMARKS: None.

ACCEPTANCE CRITERIA: For each individual specimen --

Surface Flaming (seconds)	Flaming Drip (seconds)	Damaged Length
**	2	635 mm

(** Surface Flaming values are required to be reported after removal of the 120 seconds igniting flame; however, these values are not required to be factored into determination of acceptance.)

CONCLUSION: Based on the above Results and Acceptance criteria, the item tested:

□ Complies; □ Does not comply

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the

procedures and equipment specified above.

AUG 2 6 2021

Bobby Brown

AUTHORIZED & GNATURE SGS NORTH MERICA /jab

JR

Ver. 2021-03-09 10:35

Page 2 of 2

The results contained in this report relate only to the item(s) tested. The test report shall not be reproduced except in full, without written approval from SGS North America.



Lone Henriksen

Phone: 011 45 89 53 18 60

lh@kvadrat.dk

Received:

8/9/2021

Kvadrat A/S

Fax:

Completed:

8/12/2021

Lundbergsvej 10 DK-8400 Ebeltoft

Mobile:

Code:

T

P0#: **Emall:** **Test Report:**

3-44744-0

Denmark

Key Test:

CAN/ULC-S109-14 Small Flame Test

226

Client's Identification:

Style: Casa. Content: 100% Trevira CS. Width: App. 118 inches. Finish: None. Weight Range: 16-340 g/m². Weight: 170 g/m²-16.45 oz/ly. End Use: Curtain.

Test Category: CAN/UL Small

LE 2014; V 7/21 DK

Specifier: CAN/UL

/rb /dv

TEST PERFORMED: CAN/ULC-S109-14 * - Standard for Flame Tests of Flame-Resistant Fabrics & Films, Small Flame Test

(* Note: This document was prepared and published by Underwriters' Laboratories of Canada and is approved as a National Standard of Canada.)

PRECONDITIONING:

Standard method: 0.5 hour @ 105 ± 2°C

☐ Alternate method for materials that are affected by heating to 105°C:

 \square Desiccator method: 12 hours minimum @ 20 ± 2°C and 50 ± 5% RH

☐ Alternate oven method: 1 hour @ 60 ± 2°C

APPROXIMATE AREA DENSITY OF MATERIAL (as measured by SGS North America): 155 g/m²

CONVERSION FACTORS:

 $mm \div 25.4 = inches$

 $g/m^2 \div 28.35 \times 0.0835 = oz/vd^2$

RESULTS ARE REPORTED:

☐ After 10 dry cleanings ☐ After 10 launderings

[code 226] [code 457]

[code 399]

☐ After 72 hours water leaching ☐ After scrubbing

[code 399] [code 630]

☐ After 360 hours accelerated weathering

[code 5518]

BG

Ver. 2021-03-09 10:35

Page 1 of 3

The results contained in this report relate only to the item(s) tested. The test report shall not be reproduced except in full, without written approval from SGS North America.

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/terms-e-document.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for a maximum of 45 days only.

96 Allen Boulevard Sulte D, Farmingdale, NY 11735 USA • Phone: (631) 293-8944 • Email: govmark.test.reports@sgs.com





Lone Henriksen Kvadrat A/S

Lundbergsvej 10 DK-8400 Ebeltoft

Phone: Fax:

011 45 89 53 18 60

Received:

8/9/2021

Completed:

8/12/2021

Mobile:

Code: **Test Report:**

3-44744-0

P0#:

Emall:

lh@kvadrat.dk

Denmark

Key Test:

CAN/ULC-S109-14 Small Flame Test

226

RESULTS:

Direction	Specimen #	Surface Flaming** (seconds)	Flaming Drip (seconds)	Damaged Length (mm)
	1	0	0	125
Length:	2	0	0	131
	3	0	0	120
	4	0	0	123
	5	0	0	115
			Average:	123
	6	0	0	130
	7	0	0	95
Width:	8	0	0	118
	9	0	0	112
	10	0	0	125
			Average:	116

REMARKS: None.

ACCEPTANCE CRITERIA:

	Surface Flaming (seconds)	Flaming Drip (seconds)	Damaged Length
Maximum Average:	**	Not specified	165 mm (6.5")
Maximum Individual Specimen:	**	2.0	190 mm (7.5")

(** Surface Flaming values are required to be reported after removal of the 12 seconds igniting flame; however, these values are not required to be factored into determination of acceptance.)

BG

Ver. 2021-03-09 10:35

Page 2 of 3

The results contained in this report relate only to the item(s) tested. The test report shall not be reproduced except in full, without written approval from SGS North America.

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/terms-e-document.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for a maximum of 45 days only.

96 Allen Boulevard Suite D, Farmingdale, NY 11735 USA • Phone: (631) 293-8944 • Email: govmark.test.reports@sgs.com



Lone Henriksen Kvadrat A/S

Phone: Fax:

011 45 89 53 18 60

lh@kvadrat.dk

Received:

8/9/2021

Mobile:

Completed: Code:

8/12/2021 T

PO#:

Email:

Test Report:

3-44744-0

Denmark

Key Test:

CAN/ULC-S109-14 Small Flame Test

Lundbergsvej 10 DK-8400 Ebeltoft

226

CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested:

□ Complies; □ Does not comply

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.

AUTHORIZED # GNATURE SGS NORTH MERICA

/jab

AUG 2 6 2021

Bobby Brown

RG

Ver. 2021-03-09 10:35

Page 3 of 3

The results contained in this report relate only to the item(s) tested. The test report shall not be reproduced except in full, without written approval from SGS North America. This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at



Lone Henriksen

Phone:

011 45 89 53 18 60

Received:

8/9/2021

Kvadrat A/S

Fax:

Completed:

8/13/2021

Lundbergsvej 10 DK-8400 Ebeltoft

Mobile: PO#:

Code: Test Report:

3-44744-1

E.

Email:

lh@kvadrat.dk

Denmark

Key Test:

CAN/ULC S109-14 Large Flame Test Folded Specimen

457

Client's Identification:

Style: Casa. Content: 100% Trevira CS. Width: App. 118 inches. Finish: None. Weight Range: 16-340 g/m². Weight: 170 g/m²-16.45 oz/ly. End Use: Curtain.

Test Category: CAN/UL Large Folds

LE: 2014; V 7/21 DK

Specifier: CAN/UL

/rb /dv

TEST PERFORMED: CAN/ULC-S109-14 * - Standard for Flame Tests of Flame-Resistant Fabrics & Films, Large Flame Test, Folded Specimens

(* Note: This document was prepared and published by Underwriters' Laboratories of Canada and is approved as a National Standard of Canada.)

PRECONDITIONING:

Standard method: 0.5 hour @ 105 ± 2°C

 \square Alternate method for materials that are affected by heating to 105°C:

 \square Desiccator method: 12 hours minimum @ 20 ± 2°C and 50 ± 5% RH

 \square Alternate oven method: 1 hour @ 60 ± 2°C

APPROXIMATE AREA DENSITY OF MATERIAL (as measured by SGS North America): 155 g/m²

CONVERSION FACTORS:

mm \div 25.4 = inches

 $g/m^2 \div 28.35 \times 0.0835 - oz/yd^2$

RESULTS ARE REPORTED:

☑ Initially [code 457]
 ☐ After 10 dry cleanings [code 688]
 ☐ After 10 launderings [code 630]
 ☐ After 72 hours water leaching [code 630]
 ☐ After scrubbing [code 861]
 ☐ After 360 hours accelerated weathering [code 6925]

JR

Ver. 2021-03-09 10:35

Page 1 of 2

The results contained in this report relate only to the item(s) tested. The test report shall not be reproduced except in full, without written approval from SGS North America.



Lone Henriksen

Phone:

011 45 89 53 18 60

Received:

8/9/2021

Kvadrat A/S

Fax:

Completed:

Test Report:

8/13/2021

Lundbergsvei 10 DK-8400 Ebeltoft

Mobile: PO#:

Code:

3-44744-1

Emall:

lh@kvadrat.dk

Denmark

Key Test:

CAN/ULC S109-14 Large Flame Test Folded Specimen

457

RESULTS:

Direction	Specimen #	Surface Flaming** (seconds)	Flaming Drip (seconds)	Char Length (mm)
Longth	1	0	0	25
Length:	2	0	0	48
Width:	3	0	0	39
vviatri.	4	0	0	33

REMARKS: None.

ACCEPTANCE CRITERIA: For each individual specimen --

Surface Flaming (seconds)	Flaming Drip (seconds)	Damaged Length
**	2	635 mm

(** Surface Flaming values are required to be reported after removal of the 120 seconds igniting flame; however, these values are not required to be factored into determination of acceptance.)

CONCLUSION: Based on the above Results and Acceptance criteria, the item tested:

□ Complies; □ Does not comply

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.

AUTHORIZ SGS NOR

O SIGNATURE A AMERICA

/jab

JR

AUG 2 6 2021

Bobby Brown

Ver. 2021-03-09 10:35

Page 2 of 2

The results contained in this report relate only to the item(s) tested. The test report shall not be reproduced except in full, without written approval from SGS North America.

SGS

Tested For: Lo

Lone Henriksen

Phone: 011 45 89 53 18 60

Received:

8/9/2021

S

Kvadrat A/S

Fax: Mobile: Completed:

8/17/2021

Lundbergsvej 10 DK-8400 Ebeltoft

PO#:

Code: Test Report:

3-44743-0

Email:

l: Ih@kvadrat.dk

Denmark

Key Test:

CAN/ULC-S109-14 Small Flame Test

226

Client's Identification:

Style: Pro 3. Content: 100% Trevira CS. Width: 59 inches. Finish: None. Weight Range: 16-340 g/m². Weight: 340 g/m²- 16.45

oz/ly. End Use: Curtain.

Test Category: CAN/UL Small

LE 2014; V 7/21 DK

Specifier: CAN/UL

/rb /dv

TEST PERFORMED: CAN/ULC-S109-14 * - Standard for Flame Tests of Flame-Resistant Fabrics & Films, Small Flame Test

1631

(* Note: This document was prepared and published by Underwriters' Laboratories of Canada and is approved as a National Standard of Canada.)

PRECONDITIONING:

☑ Standard method: 0.5 hour @ 105 ± 2°C

☐ Alternate method for materials that are affected by heating to 105°C:

 \square Desiccator method: 12 hours minimum @ 20 ± 2°C and 50 ± 5% RH

☐ Alternate oven method: 1 hour @ 60 ± 2°C

APPROXIMATE AREA DENSITY OF MATERIAL (as measured by SGS North America): 340 g/m²

CONVERSION FACTORS:

mm \div 25.4 = inches

 $g/m^2 \div 28.35 \times 0.0835 = oz/yd^2$

RESULTS ARE REPORTED:

⊠ Initially	[code 226]
☐ After 10 dry cleanings	[code 457]
☐ After 10 launderings	[code 399]
☐ After 72 hours water leaching	[code 399]
☐ After scrubbing	[code 630]
☐ After 360 hours accelerated weathering	[code 5518]

BG Ver. 2021-03-09 10:35

Page 1 of 3

The results contained in this report relate only to the item(s) tested. The test report shall not be reproduced except in full, without written approval from SGS North America.



Lone Henriksen

Phone: 011 45 89 53 18 60

Ih@kvadrat.dk

Received:

8/9/2021

Kvadrat A/S

Fax:

Completed:

8/17/2021

S

Lundbergsvej 10 DK-8400 Ebeltoft

Mobile: PO#:

Email:

Code: Test Report:

3-44743-0

Denmark

Key Test:

CAN/ULC-S109-14 Small Flame Test

226

RESULTS:

Direction	Specimen #	Surface Flaming** (seconds)	Flaming Drip (seconds)	Damaged Length (mm)
	1	0	0	120
	2	0	0	96
Length:	3	0	0	105
	4	0	0	108
	5	0	0	84
			Average:	103
	6	0	0	112
	7	0	0	100
Width:	8	0	0	90
	9	0	0	85
	10	0	0	90
			Average:	95

REMARKS: None.

ACCEPTANCE CRITERIA:

	Surface Flaming (seconds)	Flaming Drip (seconds)	Damaged Length
Maximum Average:	**	Not specified	165 mm (6.5")
Maximum Individual Specimen:	**	2.0	190 mm (7.5")

(** Surface Flaming values are required to be reported after removal of the 12 seconds igniting flame; however, these values are not required to be factored into determination of acceptance.)

BG

Ver. 2021-03-09 10:35

Page 2 of 3

The results contained in this report relate only to the item(s) tested. The test report shall not be reproduced except in full, without written approval from SGS North America.



Lone Henriksen

Phone: 011 45 89 53 18 60

Received:

8/9/2021

ς

Kvadrat A/S

Fax:

Completed:

Test Report:

8/17/2021

Lundbergsvej 10 DK-8400 Ebeltoft

Mobile: PO#:

Code:

3-44743-0

Email:

lh@kvadrat.dk

Denmark

Key Test:

CAN/ULC-S109-14 Small Flame Test

226

CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested:

□ Complies; □ Does not comply

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.

AUTHORIZED S NATURE SGS NORTH AMERICA /al

Bobby Brown

AUG 2 6 2021

Ver. 2021-03-09 10:35

Page 3 of 3

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/terms-e-document.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this

The results contained in this report relate only to the item(s) tested. The test report shall not be reproduced except in full, without written approval from SGS North America.

96 Allen Boulevard Suite D, Farmingdale, NY 11735 USA • Phone: (631) 293-8944 • Email: govmark.test.reports@sgs.com

only to the sample(s) tested and such sample(s) are retained for a maximum of 45 days only.

document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer

Lone Henriksen

Phone: 011 45 89 53 18 60 Received:

8/9/2021

S1

Kvadrat A/S

Fax:

Completed:

8/24/2021

Lundbergsvej 10 DK-8400 Ebeltoft

Mobile: P0#:

Code: **Test Report:**

3-44743-1

Email:

lh@kvadrat.dk

Denmark

Key Test:

CAN/ULC \$109-14 Large Flame Test Folded Specimen

457

Client's Identification:

Style: Pro 3. Content: 100% Trevira CS. Width: 59 inches. Finish: None. Weight Range: 16-340 g/m². Weight: 340 g/m²-16.45 oz/ly. End Use: Curtain.

Test Category: CAN/UL Large Folds

LE: 2014; V 7/21 DK

Specifier: CAN/UL

/rb /dv

TEST PERFORMED: CAN/ULC-S109-14 * - Standard for Flame Tests of Flame-Resistant Fabrics & Films, Large Flame Test, Folded Specimens

(* Note: This document was prepared and published by Underwriters' Laboratories of Canada and is approved as a National Standard of Canada.)

PRECONDITIONING:

☐ Alternate method for materials that are affected by heating to 105°C:

 \square Desiccator method: 12 hours minimum @ 20 ± 2°C and 50 ± 5% RH

☐ Alternate oven method: 1 hour @ 60 ± 2°C

APPROXIMATE AREA DENSITY OF MATERIAL (as measured by SGS North America): 340 g/m²

CONVERSION FACTORS:

mm \div 25.4 = inches

 $g/m^2 \div 28.35 \times 0.0835 - oz/yd^2$

RESULTS ARE REPORTED:

[code 457] ☐ After 10 dry cleanings [code 688] ☐ After 10 launderings [code 630] ☐ After 72 hours water leaching [code 630] ☐ After scrubbing [code 861] ☐ After 360 hours accelerated weathering [code 6925]

JR

Ver. 2021-03-09 10:35

Page 1 of 2

The results contained in this report relate only to the item(s) tested. The test report shall not be reproduced except in full, without written approval from SGS North America.



Lone Henriksen

Phone:

011 45 89 53 18 60

Received:

8/9/2021

S1

Kvadrat A/S

Fax:

Completed:

8/24/2021

Lundbergsvej 10 DK-8400 Ebeltoft

Mobile: PO#:

Code: **Test Report:**

3-44743-1

Emall:

Ih@kvadrat.dk

Denmark

Key Test:

CAN/ULC \$109-14 Large Flame Test Folded Specimen

457

RESULTS:

Direction	Specimen #	Surface Flaming** (seconds)	Flaming Drip (seconds)	Char Length (mm)
l anath.	1	1 0	0	185
Length:	2	0	0	114
\	3	0	0	191
Width:	4	0	0	140

REMARKS: None.

ACCEPTANCE CRITERIA: For each individual specimen ---

Surface Flaming (seconds)	Flaming Drip (seconds)	Damaged Length
**	2	635 mm

(** Surface Flaming values are required to be reported after removal of the 120 seconds igniting flame; however, these values are not required to be factored into determination of acceptance.)

CONCLUSION: Based on the above Results and Acceptance criteria, the item tested:

CERTIFICATION: I centify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.

AUTHORIZED SIGNATURE

SGS NORTH/AMERICA

/jab

JR

Alfold 202 rown

Ver. 2021-03-09 10:35

Page 2 of 2

The results contained in this report relate only to the item(s) tested. The test report shall not be reproduced except in full, without written approval from SGS North America.