# **Test Report**

Report Number: 962750-1-TEX



#### DANISH TECHNOLOGICAL INSTITUTE

Gregersensvej 1 DK-2630 Taastrup +45 72 20 20 00 info@teknologisk.dk www.teknologisk.dk

Page 1 of 3 Init.: CHF/LELN Order no.: 962750

Encl.: 2

Assignor: Kvadrat A/S, Lundbergsvej 10 , DK-8400 Ebeltoft

Material: Upholstery fabric designated: Atrium. See enclosure A for detailed sample description.

Sampling: The assignor confirms having selected the product. The product was forwarded by the

assignor and received at Danish Technological Institute on 8 January 2021.

**Period:** The test took place from 18 January 2021 to 19 January 2021.

**Method:** The test methods used are referenced in connection with the results. See enclosure B.

**Test results:** The results are shown in enclosure B.

Terms: This test was conducted accredited in accordance with international requirements (ISO/IEC

17025:2017) and in accordance with the General Terms and Conditions of Danish

Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent.

Place: Danish Technological Institute, Taastrup, Building and Construction

Signature: This document is only valid with a digital signature from Danish Technological Institute. The

date of issue appears from the digital signature.

Charlotte Fischer Senior Consultant



DANISH TECHNOLOGICAL INSTITUTE







## Sample

Description: Upholstery fabric

Designated: Atrium.

Fibre content: 100% Trevira CS. (as per info from the assigner).

Photo:





#### **Results**

### Test of Upholstery fabric designated: Atrium

Determination of the slippage resistance of yarns at a seam in woven fabrics - Fixed load method

EN ISO 13936-2:2004

Test conditions: 21°C, 65% RH

| Performed on  | Load [N] | Seam parallel to warp       | Seam parallel to weft       |
|---------------|----------|-----------------------------|-----------------------------|
| Standard seam | 180      | 3 mm seam opening           | 2 mm seam opening           |
|               |          | Average of 5 determinations | Average of 5 determinations |