

Received: 11/04/2014 Completed: 11/07/2014 Letter: V JS P.O.#: MEMORY Test Report #: 3-05069-0

Client's Identification Style: Memory by Kvadrat.

Tested For: **Anna King**
Maharam
74 Horseblock Road
Yaphank, NY 11980

Key Test: NFPA 701-2010 TM#1 190
Tel: 1-(631)-282-6318 Ext:
Fax: 1-(631)-282-6410

PC: 0.5H DL/jd

TEST PERFORMED: NFPA 701 - Standard Methods of Fire Tests for Flame Propagation of Textiles and Films - 2010 Edition - Test Method #1

AS CITED BY: ACT Voluntary Performance Guidelines (August 2010)

PRODUCT CONFIGURATION: Single Layer; Multi Layer

RESULTS REPORTED: Initially; After 3 dry cleanings; After 5 launderings @ 160°F

RESULTS:

Specimen #	Afterflame* (seconds)	Flaming Drip (seconds)	Weight Loss (percent)
1	0	0	21.6
2	0	0	18.9
3	0	0	14.7
4	0	0	23.1
5	0	0	16.4
6	0	0	16.4
7	0	0	7.7
8	0	0	14.4
9	0	0	18.5
10	0	0	15.8
	Mean: 0	Mean: 0	16.8

STATISTICAL VALUES: SD = 4.3 3 SD = 12.9 Mean + 3 SD = 29.6

ABBREVIATIONS USED: SD = Standard deviation. NT = Not tested.

APPROXIMATE WEIGHT OF MATERIAL (as measured by Govmark): 479 g/m²

PRECONDITIONING: 0.5 hr @ 220°F (Standard)
 24 hrs @ 68±9°F (Alternate: Material shrinks/distorts @ 220°F)

CONVERSION FACTOR: g/m² ÷ 28.35 x .835 = oz/yd²

NOTE:

1. All specimens prepared in the length direction.
2. See addendum for individual specimen weights.

Received: 11/04/2014 Completed: 11/07/2014 Letter: V JS P.O.#: MEMORY Test Report #: 3-05069-0-

Client's Identification Style: Memory by Kvadrat.

Tested For: **Anna King** Key Test: NFPA 701-2010 TM#1 190
Maharam
74 Horseblock Road Tel: 1-(631)-282-6318 Ext:
Yaphank, NY 11980 Fax: 1-(631)-282-6410

REMARKS:

- Flames did not project above the top of the specimen.
- Flames projected above the top of the specimen; Specimen #'s _____
- Other: _____

FAILURE CRITERIA: As cited by NFPA 701 - 2010 Edition Test Method #1

Afterflame	Flaming Drip (Mean)	Weight Loss (percent)	
		Mean	Individual Specimen
*	Exceeds 2 seconds	Exceeds 40%	Exceeds Mean + 3 SD**

CONCLUSION: Based on the Results on page 1 and the above Failure Criteria cited by NFPA 701 - 2010 Edition Test Method #1, the item tested:

- Passes; Fails; Requires testing of 10 additional specimens
i.e. only one individual specimen failure was noted

* Afterflame is required to be recorded; however, the NFPA document does not factor it into the Failure Criteria reporting requirements. It should be noted that excessive afterflames (15 seconds or more) could be cause for rejection by local fire authorities performing "match" field tests.

** See "Discussion" on Page 3.

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by NFPA 701 - 2010 Edition Test Method #1.

NOV 11 2014

AUTHORIZED SIGNATURE
THE GOVMARK ORGANIZATION, INC. /je /gb

MS. PHYLLIS PETTIT

Received: 11/04/2014	Completed: 11/07/2014	Letter: V	JS	P.O.#: MEMORY	Test Report #:	3-05069-0-
Client's Identification	Style: Memory by Kvadrat.					
Tested For: Anna King Maharam 74 Horseblock Road Yaphank, NY 11980			Key Test: NFPA 701-2010 TM#1			190
			Tel: 1-(631)-282-6318		Ext:	
			Fax: 1-(631)-282-6410			

** DISCUSSION:

Weight Loss - Individual Specimen Failure:

The NFPA 701 document, as written, provides for a statistical calculation which provides for retest and a potential failure if any individual value exceeds the mean by three standard deviations. Govmark is of the opinion that this cannot mathematically occur, i.e. no individual result is mathematically capable of exceeding the mean plus three standard deviations. Therefore, in effect, Govmark is of the opinion that this "individual specimen criteria" has no meaning, since it cannot possibly result in a nonconformance.

Client Name : MAHARAM
Addendum to Test Report # : 3-05069-0-V
Test : NFFPA 701

<u>Specimen #</u>	<u>Weight Before Test (g)</u>	<u>Weight After Test (g)</u>	<u>Percent Weight Loss</u>
1	29.60	23.20	21.6
2	29.60	24.00	18.9
3	30.00	25.60	14.7
4	29.40	22.60	23.1
5	29.20	24.40	16.4
6	29.20	24.40	16.4
7	28.60	26.40	7.7
8	29.20	25.00	14.4
9	29.20	23.80	18.5
10	29.20	24.60	15.8

Mean Percent Weight Loss : 16.8
Standard Deviation : 4.3
3 x Standard Deviation : 12.9
Mean + 3 x Standard Deviation : 29.6

NOV 11 2014
