

**Tested For:** Lone Henriksen  
Kvadrat A/S  
Lundbergsvej 10 DK-8400 Ebeltoft  
  
Denmark

**Phone:** 011 45 89 53 18 60  
**Fax:**  
**Mobile:**  
**PO#:**  
**Email:** lh@kvadrat.dk

**Received:** 8/9/2021  
**Completed:** 8/13/2021  
**Code:** U  
**Test Report:** 3-44745-0

**Key Test:** CAN/ULC-S109-14 Small Flame Test

226

**Client's Identification:**

Style: Waver. Content: 100% Trevira CS. Width: App. 118 inches. Finish: None. Weight Range: 16-340 g/m<sup>2</sup>. Weight: 16 g/m<sup>2</sup>-1.52 oz/ly. End Use: Curtain.

Test Category: CAN/UL Small LE 2014; V 7/21 DK Specifier: CAN/UL /rb /dv

TEST PERFORMED: CAN/ULC-S109-14 \* - Standard for Flame Tests of Flame-Resistant Fabrics & Films, Small Flame Test

(\* Note: This document was prepared and published by Underwriters' Laboratories of Canada and is approved as a National Standard of Canada.)

**PRECONDITIONING:**

- ☒ Standard method: 0.5 hour @ 105 ± 2°C
- ☐ Alternate method for materials that are affected by heating to 105°C:
  - ☐ Desiccator method: 12 hours minimum @ 20 ± 2°C and 50 ± 5% RH
  - ☐ Alternate oven method: 1 hour @ 60 ± 2°C

APPROXIMATE AREA DENSITY OF MATERIAL (as measured by SGS North America): 43.5 g/m<sup>2</sup>

CONVERSION FACTORS: mm ÷ 25.4 = inches  
g/m<sup>2</sup> ÷ 28.35 x 0.0835 = oz/yd<sup>2</sup>

**RESULTS ARE REPORTED:**

- ☒ Initially [code 226]
- ☐ After 10 dry cleanings [code 457]
- ☐ After 10 launderings [code 399]
- ☐ After 72 hours water leaching [code 399]
- ☐ After scrubbing [code 630]
- ☐ After 360 hours accelerated weathering [code 5518]

The results contained in this report relate only to the item(s) tested. The test report shall not be reproduced except in full, without written approval from SGS North America.

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/terms-e-document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for a maximum of 45 days only.

**Tested For:** Lone Henriksen  
Kvadrat A/S  
Lundbergsvej 10 DK-8400 Ebeltøft

**Phone:** 011 45 89 53 18 60  
**Fax:**  
**Mobile:**  
**PO#:**  
**Email:** lh@kvadrat.dk

**Received:** 8/9/2021  
**Completed:** 8/13/2021  
**Code:** U  
**Test Report:** 3-44745-0

Denmark

**Key Test:** CAN/ULC-S109-14 Small Flame Test

226

## RESULTS:

Direction	Specimen #	Surface Flaming** (seconds)	Flaming Drip (seconds)	Damaged Length (mm)
Length:	1	0	0	140
	2	0	0	110
	3	0	0	130
	4	0	0	170
	5	0	0	135
	Average:			137
Width:	6	0	0	155
	7	0	0	185
	8	0	0	133
	9	0	0	155
	10	0	0	155
	Average:			157

REMARKS: None.

## ACCEPTANCE CRITERIA:

	Surface Flaming (seconds)	Flaming Drip (seconds)	Damaged Length
Maximum Average:	**	Not specified	165 mm (6.5")
Maximum Individual Specimen:	**	2.0	190 mm (7.5")

(\*\* Surface Flaming values are required to be reported after removal of the 12 seconds igniting flame; however, these values are not required to be factored into determination of acceptance.)

The results contained in this report relate only to the item(s) tested. The test report shall not be reproduced except in full, without written approval from SGS North America.

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/terms-e-document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for a maximum of 45 days only.



**Tested For:** Lone Henriksen  
Kvadrat A/S  
Lundbergsvej 10 DK-8400 Ebeltøft

**Phone:** 011 45 89 53 18 60  
**Fax:**  
**Mobile:**  
**PO#:**  
**Email:** lh@kvadrat.dk

**Received:** 8/9/2021  
**Completed:** 8/13/2021  
**Code:** U  
**Test Report:** 3-44745-0

Denmark

**Key Test:** CAN/ULC-S109-14 Small Flame Test

226

**CONCLUSION:** Based on the above Results and Acceptance Criteria, the item tested:

☒ Complies; ☐ Does not comply

**CERTIFICATION:** I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.

AUTHORIZED SIGNATURE  
SGS NORTH AMERICA

/jab

/al

AUG 26 2021

*Bobby Brown*

**Tested For:** Lone Henriksen  
Kvadrat A/S  
Lundbergsvej 10 DK-8400 Ebeltoft

**Phone:** 011 45 89 53 18 60  
**Fax:**  
**Mobile:**  
**PO#:**  
**Email:** lh@kvadrat.dk

**Received:** 8/9/2021  
**Completed:** 8/16/2021  
**Code:** U1  
**Test Report:** 3-44745-1

Denmark

**Key Test:** CAN/ULC S109-14 Large Flame Test Folded Specimen

457

**Client's Identification:**

Style: Waver. Content: 100% Trevira CS. Width: App. 118 inches. Finish: None. Weight Range: 16-340g/m<sup>2</sup>. Weight: 16 g/m<sup>2</sup>- 1.52 oz/ly. End Use: Curtain.

Test Category: CAN/UL Large Folds

LE: 2014; V 7/21 DK

Specifier: CAN/UL

/rb /dv

TEST PERFORMED: CAN/ULC-S109-14 \* - Standard for Flame Tests of Flame-Resistant Fabrics & Films, Large Flame Test, Folded Specimens

(\* Note: This document was prepared and published by Underwriters' Laboratories of Canada and is approved as a National Standard of Canada.)

**PRECONDITIONING:**

- ☐ Standard method: 0.5 hour @ 105 ± 2°C
- ☒ Alternate method for materials that are affected by heating to 105°C:
  - ☒ Desiccator method: 12 hours minimum @ 20 ± 2°C and 50 ± 5% RH
  - ☐ Alternate oven method: 1 hour @ 60 ± 2°C

APPROXIMATE AREA DENSITY OF MATERIAL (as measured by SGS North America): 43.5 g/m<sup>2</sup>

**CONVERSION FACTORS:**

mm ÷ 25.4 = inches  
g/m<sup>2</sup> ÷ 28.35 x 0.0835 = oz/yd<sup>2</sup>

**RESULTS ARE REPORTED:**

- ☒ Initially [code 457]
- ☐ After 10 dry cleanings [code 688]
- ☐ After 10 launderings [code 630]
- ☐ After 72 hours water leaching [code 630]
- ☐ After scrubbing [code 861]
- ☐ After 360 hours accelerated weathering [code 6925]

The results contained in this report relate only to the item(s) tested. The test report shall not be reproduced except in full, without written approval from SGS North America.

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/terms-e-document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for a maximum of 45 days only.



**Tested For:** Lone Henriksen  
Kvadrat A/S  
Lundbergsvej 10 DK-8400 Ebeltøft

**Phone:** 011 45 89 53 18 60  
**Fax:**  
**Mobile:**  
**PO#:**  
**Email:** lh@kvadrat.dk

**Received:** 8/9/2021  
**Completed:** 8/16/2021  
**Code:** U1  
**Test Report:** 3-44745-1

Denmark

**Key Test:** CAN/ULC S109-14 Large Flame Test Folded Specimen

457

## RESULTS:

Direction	Specimen #	Surface Flaming** (seconds)	Flaming Drip (seconds)	Char Length (mm)
Length:	1	0	0	56
	2	0	0	69
Width:	3	0	0	77
	4	0	0	74

REMARKS: None.

ACCEPTANCE CRITERIA: For each individual specimen --

Surface Flaming (seconds)	Flaming Drip (seconds)	Damaged Length
**	2	635 mm

(\*\* Surface Flaming values are required to be reported after removal of the 120 seconds igniting flame; however, these values are not required to be factored into determination of acceptance.)

CONCLUSION: Based on the above Results and Acceptance criteria, the item tested:

☒ Complies; ☐ Does not comply

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.

AUTHORIZED SIGNATURE  
SGS NORTH AMERICA  
/jab

AUG 26 2021  
*Bobby Brown*

The results contained in this report relate only to the item(s) tested. The test report shall not be reproduced except in full, without written approval from SGS North America.

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/terms-e-document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for a maximum of 45 days only.

**Tested For:** Lone Henriksen  
Kvadrat A/S  
Lundbergsvej 10 DK-8400 Ebeltøft  
  
Denmark

**Phone:** 011 45 89 53 18 60  
**Fax:**  
**Mobile:**  
**PO#:**  
**Email:** lh@kvadrat.dk

**Received:** 8/9/2021  
**Completed:** 8/12/2021  
**Code:** T  
**Test Report:** 3-44744-0

**Key Test:** CAN/ULC-S109-14 Small Flame Test

226

**Client's Identification:**

Style: Casa. Content: 100% Trevira CS. Width: App. 118 inches. Finish: None. Weight Range: 16-340 g/m<sup>2</sup>. Weight: 170 g/m<sup>2</sup>-16.45 oz/ly. End Use: Curtain.

Test Category: CAN/UL Small LE 2014; V 7/21 DK Specifier: CAN/UL /rb /dv

TEST PERFORMED: CAN/ULC-S109-14 \* - Standard for Flame Tests of Flame-Resistant Fabrics & Films, Small Flame Test

(\* Note: This document was prepared and published by Underwriters' Laboratories of Canada and is approved as a National Standard of Canada.)

**PRECONDITIONING:**

- ☒ Standard method: 0.5 hour @ 105 ± 2°C
- ☐ Alternate method for materials that are affected by heating to 105°C:
  - ☐ Desiccator method: 12 hours minimum @ 20 ± 2°C and 50 ± 5% RH
  - ☐ Alternate oven method: 1 hour @ 60 ± 2°C

APPROXIMATE AREA DENSITY OF MATERIAL (as measured by SGS North America): 155 g/m<sup>2</sup>

CONVERSION FACTORS: mm ÷ 25.4 = inches  
g/m<sup>2</sup> ÷ 28.35 x 0.0835 = oz/yd<sup>2</sup>

**RESULTS ARE REPORTED:**

- ☒ Initially [code 226]
- ☐ After 10 dry cleanings [code 457]
- ☐ After 10 launderings [code 399]
- ☐ After 72 hours water leaching [code 399]
- ☐ After scrubbing [code 630]
- ☐ After 360 hours accelerated weathering [code 5518]

The results contained in this report relate only to the item(s) tested. The test report shall not be reproduced except in full, without written approval from SGS North America.

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/terms-e-document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for a maximum of 45 days only.



**Tested For:** Lone Henriksen  
Kvadrat A/S  
Lundbergsvej 10 DK-8400 Ebeltoft

**Phone:** 011 45 89 53 18 60  
**Fax:**  
**Mobile:**  
**PO#:**  
**Email:** lh@kvadrat.dk

**Received:** 8/9/2021  
**Completed:** 8/12/2021  
**Code:** T  
**Test Report:** 3-44744-0

Denmark

**Key Test:** CAN/ULC-S109-14 Small Flame Test

226

## RESULTS:

Direction	Specimen #	Surface Flaming** (seconds)	Flaming Drip (seconds)	Damaged Length (mm)
Length:	1	0	0	125
	2	0	0	131
	3	0	0	120
	4	0	0	123
	5	0	0	115
	Average:			123
Width:	6	0	0	130
	7	0	0	95
	8	0	0	118
	9	0	0	112
	10	0	0	125
	Average:			116

REMARKS: None.

## ACCEPTANCE CRITERIA:

	Surface Flaming (seconds)	Flaming Drip (seconds)	Damaged Length
Maximum Average:	**	Not specified	165 mm (6.5")
Maximum Individual Specimen:	**	2.0	190 mm (7.5")

(\*\* Surface Flaming values are required to be reported after removal of the 12 seconds igniting flame; however, these values are not required to be factored into determination of acceptance.)

The results contained in this report relate only to the item(s) tested. The test report shall not be reproduced except in full, without written approval from SGS North America.

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/terms-e-document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for a maximum of 45 days only.

**Tested For:** Lone Henriksen  
Kvadrat A/S  
Lundbergsvej 10 DK-8400 Ebeltøft

**Phone:** 011 45 89 53 18 60  
**Fax:**  
**Mobile:**  
**PO#:**  
**Email:** lh@kvadrat.dk

**Received:** 8/9/2021  
**Completed:** 8/12/2021  
**Code:** T  
**Test Report:** 3-44744-0

Denmark

**Key Test:** CAN/ULC-S109-14 Small Flame Test

226

**CONCLUSION:** Based on the above Results and Acceptance Criteria, the item tested:

☒ Complies; ☐ Does not comply

**CERTIFICATION:** I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.

AUTHORIZED SIGNATURE  
SGS NORTH AMERICA  
/jab

AUG 26 2021

*Bobby Brown*

The results contained in this report relate only to the item(s) tested. The test report shall not be reproduced except in full, without written approval from SGS North America.

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/terms-e-document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for a maximum of 45 days only.



<b>Tested For:</b>	<b>Lone Henriksen</b>	<b>Phone:</b>	<b>011 45 89 53 18 60</b>	<b>Received:</b>	<b>8/9/2021</b>
	<b>Kvadrat A/S</b>	<b>Fax:</b>		<b>Completed:</b>	<b>8/13/2021</b>
	<b>Lundbergsvej 10 DK-8400 Ebeltøft</b>	<b>Mobile:</b>		<b>Code:</b>	<b>T1</b>
		<b>PO#:</b>		<b>Test Report:</b>	<b>3-44744-1</b>
		<b>Email:</b>	<b>lh@kvadrat.dk</b>		
	<b>Denmark</b>				

**Key Test:** CAN/ULC S109-14 Large Flame Test Folded Specimen

457

**Client's Identification:**

Style: Casa. Content: 100% Trevira CS. Width: App. 118 inches. Finish: None. Weight Range: 16-340 g/m<sup>2</sup>. Weight: 170 g/m<sup>2</sup>-16.45 oz/ly. End Use: Curtain.

Test Category: CAN/UL Large Folds LE: 2014; V 7/21 DK Specifier: CAN/UL /rb /dv  
**TEST PERFORMED:** CAN/ULC-S109-14 \* - Standard for Flame Tests of Flame-Resistant Fabrics & Films, Large Flame Test, Folded Specimens

(\* Note: This document was prepared and published by Underwriters' Laboratories of Canada and is approved as a National Standard of Canada.)

**PRECONDITIONING:**

- ☒ Standard method: 0.5 hour @ 105 ± 2°C
- ☐ Alternate method for materials that are affected by heating to 105°C:
  - ☐ Desiccator method: 12 hours minimum @ 20 ± 2°C and 50 ± 5% RH
  - ☐ Alternate oven method: 1 hour @ 60 ± 2°C

**APPROXIMATE AREA DENSITY OF MATERIAL** (as measured by SGS North America): 155 g/m<sup>2</sup>

**CONVERSION FACTORS:**

mm ÷ 25.4 = inches  
 g/m<sup>2</sup> ÷ 28.35 x 0.0835 = oz/yd<sup>2</sup>

**RESULTS ARE REPORTED:**

- ☒ Initially [code 457]
- ☐ After 10 dry cleanings [code 688]
- ☐ After 10 launderings [code 630]
- ☐ After 72 hours water leaching [code 630]
- ☐ After scrubbing [code 861]
- ☐ After 360 hours accelerated weathering [code 6925]

The results contained in this report relate only to the item(s) tested. The test report shall not be reproduced except in full, without written approval from SGS North America.

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/terms-e-document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for a maximum of 45 days only.

**Tested For:** Lone Henriksen  
Kvadrat A/S  
Lundbergsvej 10 DK-8400 Ebeltøft

**Phone:** 011 45 89 53 18 60  
**Fax:**  
**Mobile:**  
**PO#:**  
**Email:** lh@kvadrat.dk

**Received:** 8/9/2021  
**Completed:** 8/13/2021  
**Code:** T1  
**Test Report:** 3-44744-1

Denmark

**Key Test:** CAN/ULC S109-14 Large Flame Test Folded Specimen

457

## RESULTS:

Direction	Specimen #	Surface Flaming** (seconds)	Flaming Drip (seconds)	Char Length (mm)
Length:	1	0	0	25
	2	0	0	48
Width:	3	0	0	39
	4	0	0	33

REMARKS: None.

ACCEPTANCE CRITERIA: For each individual specimen --

Surface Flaming (seconds)	Flaming Drip (seconds)	Damaged Length
**	2	635 mm

(\*\* Surface Flaming values are required to be reported after removal of the 120 seconds igniting flame; however, these values are not required to be factored into determination of acceptance.)

CONCLUSION: Based on the above Results and Acceptance criteria, the item tested:

☒ Complies; ☐ Does not comply

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.

AUTHORIZED SIGNATURE  
SGS NORTH AMERICA  
/jab

AUG 26 2021

Bobby Brown

JR

Ver. 2021-03-09 10:35

Page 2 of 2

The results contained in this report relate only to the item(s) tested. The test report shall not be reproduced except in full, without written approval from SGS North America.

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/terms-e-document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for a maximum of 45 days only.

96 Allen Boulevard Suite D, Farmingdale, NY 11735 USA • Phone: (631) 293-8944 • Email: [govmark.test.reports@sgs.com](mailto:govmark.test.reports@sgs.com)





**Tested For:** Lone Henriksen  
Kvadrat A/S  
Lundbergsvej 10 DK-8400 Ebeltøft

**Phone:** 011 45 89 53 18 60  
**Fax:**  
**Mobile:**  
**PO#:**  
**Email:** lh@kvadrat.dk

**Received:** 8/9/2021  
**Completed:** 8/17/2021  
**Code:** S  
**Test Report:** 3-44743-0

Denmark

**Key Test:** CAN/ULC-S109-14 Small Flame Test

226

**Client's Identification:**

Style: Pro 3. Content: 100% Trevira CS. Width: 59 inches. Finish: None. Weight Range: 16-340 g/m<sup>2</sup>. Weight: 340 g/m<sup>2</sup>- 16.45 oz/ly. End Use: Curtain.

Test Category: CAN/UL Small

LE 2014; V 7/21 DK

Specifier: CAN/UL

/rb /dv

**TEST PERFORMED:** CAN/ULC-S109-14 \* - Standard for Flame Tests of Flame-Resistant Fabrics & Films, Small Flame Test

(\* Note: This document was prepared and published by Underwriters' Laboratories of Canada and is approved as a National Standard of Canada.)

**PRECONDITIONING:**

- ☒ Standard method: 0.5 hour @ 105 ± 2°C
- ☐ Alternate method for materials that are affected by heating to 105°C:
  - ☐ Desiccator method: 12 hours minimum @ 20 ± 2°C and 50 ± 5% RH
  - ☐ Alternate oven method: 1 hour @ 60 ± 2°C

**APPROXIMATE AREA DENSITY OF MATERIAL** (as measured by SGS North America): 340 g/m<sup>2</sup>

**CONVERSION FACTORS:**      mm ÷ 25.4 = inches  
   g/m<sup>2</sup> ÷ 28.35 x 0.0835 = oz/yd<sup>2</sup>

**RESULTS ARE REPORTED:**

- ☒ Initially [code 226]
- ☐ After 10 dry cleanings [code 457]
- ☐ After 10 launderings [code 399]
- ☐ After 72 hours water leaching [code 399]
- ☐ After scrubbing [code 630]
- ☐ After 360 hours accelerated weathering [code 5518]

The results contained in this report relate only to the item(s) tested. The test report shall not be reproduced except in full, without written approval from SGS North America.

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/terms-e-document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for a maximum of 45 days only.

**Tested For:** Lone Henriksen  
Kvadrat A/S  
Lundbergsvej 10 DK-8400 Ebeltøft

Denmark

**Phone:** 011 45 89 53 18 60  
**Fax:**  
**Mobile:**  
**PO#:**  
**Email:** lh@kvadrat.dk

**Received:** 8/9/2021  
**Completed:** 8/17/2021  
**Code:** S  
**Test Report:** 3-44743-0

**Key Test:** CAN/ULC-S109-14 Small Flame Test

226

## RESULTS:

Direction	Specimen #	Surface Flaming** (seconds)	Flaming Drip (seconds)	Damaged Length (mm)
Length:	1	0	0	120
	2	0	0	96
	3	0	0	105
	4	0	0	108
	5	0	0	84
	Average:			103
Width:	6	0	0	112
	7	0	0	100
	8	0	0	90
	9	0	0	85
	10	0	0	90
	Average:			95

REMARKS: None.

## ACCEPTANCE CRITERIA:

	Surface Flaming (seconds)	Flaming Drip (seconds)	Damaged Length
Maximum Average:	**	Not specified	165 mm (6.5")
Maximum Individual Specimen:	**	2.0	190 mm (7.5")

(\*\* Surface Flaming values are required to be reported after removal of the 12 seconds igniting flame; however, these values are not required to be factored into determination of acceptance.)

The results contained in this report relate only to the item(s) tested. The test report shall not be reproduced except in full, without written approval from SGS North America.

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/terms-e-document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for a maximum of 45 days only.



**Tested For:** Lone Henriksen  
Kvadrat A/S  
Lundbergsvej 10 DK-8400 Ebeltøft  
  
Denmark

**Phone:** 011 45 89 53 18 60  
**Fax:**  
**Mobile:**  
**PO#:**  
**Email:** lh@kvadrat.dk

**Received:** 8/9/2021  
**Completed:** 8/17/2021  
**Code:** S  
**Test Report:** 3-44743-0

**Key Test:** CAN/ULC-S109-14 Small Flame Test

226

**CONCLUSION:** Based on the above Results and Acceptance Criteria, the item tested:

☒ Complies; ☐ Does not comply

**CERTIFICATION:** I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.

AUTHORIZED SIGNATURE  
SGS NORTH AMERICA  
/jab /al

*Bobby Brown*

AUG 26 2021

The results contained in this report relate only to the item(s) tested. The test report shall not be reproduced except in full, without written approval from SGS North America. This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/terms-e-document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for a maximum of 45 days only.

**Tested For:** Lone Henriksen  
Kvadrat A/S  
Lundbergsvej 10 DK-8400 Ebeltøft

**Phone:** 011 45 89 53 18 60  
**Fax:**  
**Mobile:**  
**PO#:**  
**Email:** lh@kvadrat.dk

**Received:** 8/9/2021  
**Completed:** 8/24/2021  
**Code:** S1  
**Test Report:** 3-44743-1

Denmark

**Key Test:** CAN/ULC S109-14 Large Flame Test Folded Specimen

457

**Client's Identification:**

Style: Pro 3. Content: 100% Trevira CS. Width: 59 inches. Finish: None. Weight Range: 16- 340 g/m<sup>2</sup>. Weight: 340 g/m<sup>2</sup>- 16.45 oz/ly. End Use: Curtain.

Test Category: CAN/UL Large Folds

LE: 2014; V 7/21 DK

Specifier: CAN/UL

/rb /dv

TEST PERFORMED: CAN/ULC-S109-14 \* - Standard for Flame Tests of Flame-Resistant Fabrics & Films, Large Flame Test, Folded Specimens

(\* Note: This document was prepared and published by Underwriters' Laboratories of Canada and is approved as a National Standard of Canada.)

**PRECONDITIONING:**

- ☒ Standard method: 0.5 hour @ 105 ± 2°C
- ☐ Alternate method for materials that are affected by heating to 105°C:
  - ☐ Desiccator method: 12 hours minimum @ 20 ± 2°C and 50 ± 5% RH
  - ☐ Alternate oven method: 1 hour @ 60 ± 2°C

APPROXIMATE AREA DENSITY OF MATERIAL (as measured by SGS North America): 340 g/m<sup>2</sup>

**CONVERSION FACTORS:**

mm ÷ 25.4 = inches  
g/m<sup>2</sup> ÷ 28.35 x 0.0835 = oz/yd<sup>2</sup>

**RESULTS ARE REPORTED:**

- ☒ Initially [code 457]
- ☐ After 10 dry cleanings [code 688]
- ☐ After 10 launderings [code 630]
- ☐ After 72 hours water leaching [code 630]
- ☐ After scrubbing [code 861]
- ☐ After 360 hours accelerated weathering [code 6925]

The results contained in this report relate only to the item(s) tested. The test report shall not be reproduced except in full, without written approval from SGS North America.

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/terms-e-document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for a maximum of 45 days only.



**Tested For:** Lone Henriksen  
Kvadrat A/S  
Lundbergsvej 10 DK-8400 Ebeltøft

**Phone:** 011 45 89 53 18 60  
**Fax:**  
**Mobile:**  
**PO#:**  
**Email:** lh@kvadrat.dk

**Received:** 8/9/2021  
**Completed:** 8/24/2021  
**Code:** S1  
**Test Report:** 3-44743-1

Denmark

**Key Test:** CAN/ULC S109-14 Large Flame Test Folded Specimen

457

**RESULTS:**

Direction	Specimen #	Surface Flaming** (seconds)	Flaming Drip (seconds)	Char Length (mm)
Length:	1	0	0	185
	2	0	0	114
Width:	3	0	0	191
	4	0	0	140

**REMARKS:** None.

**ACCEPTANCE CRITERIA:** For each individual specimen --

Surface Flaming (seconds)	Flaming Drip (seconds)	Damaged Length
**	2	635 mm

(\*\* Surface Flaming values are required to be reported after removal of the 120 seconds igniting flame; however, these values are not required to be factored into determination of acceptance.)

**CONCLUSION:** Based on the above Results and Acceptance criteria, the item tested:

☒ Complies; ☐ Does not comply

**CERTIFICATION:** I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.

AUTHORIZED SIGNATURE  
SGS NORTH AMERICA  
/jab

AUG 26 2021  
Bobby Brown

The results contained in this report relate only to the item(s) tested. The test report shall not be reproduced except in full, without written approval from SGS North America.

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/terms-e-document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for a maximum of 45 days only.