

EN 29053 - Determination of airflow resistance

Direct airflow method - method A


Client: Kinnasand

Date: 12-12-19

Type: Aerio, Zone 100% Polyester FR
Colour: 14, 25
Order:
Batch:
Manufacturer: Kinnasand

Specimen Diameter: 100 mm
Thickness: 0.4 mm
Area specific mass: 74 g/m²

u_l (mm/s)	$R_{s,l}$ (Pa s/m)
16.53	0
14.16	0
11.80	0
9.44	0
7.12	0
4.42	0



Airflow Resistance

$R_s = <10$ Pa s/m