

EN 29053 - Determination of airflow resistance

Direct airflow method - method A


Client: Febrik / kvadrat

Date: 19/10/2021

Fabric details
Type: Mizmaze
Colour: 762
Project:
Pick:
Manufacturer: Kvadrat

Specimen
Diameter: 100 mm
Thickness: 2.06 mm
Area specific mass: 633 g/m²

u_l (mm/s)	$R_s l$ (Pa s/m)
16.53	289
14.16	291
11.80	294
9.44	297
7.12	298
4.80	295



Airflow Resistance

$R_s = 301$ Pa s/m