

Test Report

Revision 1

Report Number:
114216-1-TEX rev. 1



**DANISH
TECHNOLOGICAL
INSTITUTE**

Gregersensvej 1
DK-2630 Taastrup
+45 72 20 20 00
info@teknologisk.dk
www.teknologisk.dk

Page 1 of 8
Init.: CHF/LELN
Order no.: 114216
Encl.: 0

Assignor: KVADRAT A/S, Lundbergsvej 10, DK-8400 Ebeltoft

Material: Sample of upholstery fabric designated: Harald 3. See page 2 for detailed sample description.

Sampling: The assignor confirms having selected the product. The product was forwarded by the assignor and received at Danish Technological Institute on 10 December 2021.

Period: The test took place from 13 December 2021 to 15 March 2022.

Method: The test methods used are referenced in connection with the results. See page 7.

Test results: The results are shown on page 7.

Remarks: This report replaces Report no. 114216-1 of 05.01.2022. sample 0133 and 0182 has been reevaluated and the results have been changed.

Terms: This test was conducted accredited in accordance with international requirements (ISO/IEC 17025:2017) and in accordance with the General Terms and Conditions of Danish Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent.

Place: Danish Technological Institute, Taastrup, Environmental Technology

Signature: This document is only valid with a digital signature from Danish Technological Institute. The date of issue appears from the digital signature.

Charlotte Fischer
Senior Consultant



DIGITALLY SIGNED DOCUMENT

15 March 2022

DANISH TECHNOLOGICAL INSTITUTE









DANAK

TEST Reg.no. 2



Samples

Sample mark	Description	Photo
123	Upholstery fabric Designated: Harald 3 Fibre content: 100% Cotton	
133	Upholstery fabric Designated: Harald 3 Fibre content: 100% Cotton	
143	Upholstery fabric Designated: Harald 3 Fibre content: 100% Cotton	
182	Upholstery fabric Designated: Harald 3 Fibre content: 100% Cotton	
192	Upholstery fabric Designated: Harald 3 Fibre content: 100% Cotton	
212	Upholstery fabric Designated: Harald 3 Fibre content: 100% Cotton	









Samples (continued)

Sample mark	Description	Photo
233	Upholstery fabric Designated: Harald 3 Fibre content: 100% Cotton	
242	Upholstery fabric Designated: Harald 3 Fibre content: 100% Cotton	
283	Upholstery fabric Designated: Harald 3 Fibre content: 100% Cotton	
343	Upholstery fabric Designated: Harald 3 Fibre content: 100% Cotton	
382	Upholstery fabric Designated: Harald 3 Fibre content: 100% Cotton	
423	Upholstery fabric Designated: Harald 3 Fibre content: 100% Cotton	



Samples (*continued*)

Sample mark	Description	Photo
432	Upholstery fabric Designated: Harald 3 Fibre content: 100% Cotton	
443	Upholstery fabric Designated: Harald 3 Fibre content: 100% Cotton	
512	Upholstery fabric Designated: Harald 3 Fibre content: 100% Cotton	
533	Upholstery fabric Designated: Harald 3 Fibre content: 100% Cotton	
543	Upholstery fabric Designated: Harald 3 Fibre content: 100% Cotton	
552	Upholstery fabric Designated: Harald 3 Fibre content: 100% Cotton	



Samples (*continued*)

Sample mark	Description	Photo
582	Upholstery fabric Designated: Harald 3 Fibre content: 100% Cotton	
612	Upholstery fabric Designated: Harald 3 Fibre content: 100% Cotton	
632	Upholstery fabric Designated: Harald 3 Fibre content: 100% Cotton	
652	Upholstery fabric Designated: Harald 3 Fibre content: 100% Cotton	
692	Upholstery fabric Designated: Harald 3 Fibre content: 100% Cotton	
722	Upholstery fabric Designated: Harald 3 Fibre content: 100% Cotton	



Samples (*continued*)

Sample mark	Description	Photo
772	Upholstery fabric Designated: Harald 3 Fibre content: 100% Cotton	
792	Upholstery fabric Designated: Harald 3 Fibre content: 100% Cotton	
823	Upholstery fabric Designated: Harald 3 Fibre content: 100% Cotton	
942	Upholstery fabric Designated: Harald 3 Fibre content: 100% Cotton	
952	Upholstery fabric Designated: Harald 3 Fibre content: 100% Cotton	
982	Upholstery fabric Designated: Harald 3 Fibre content: 100% Cotton	



Results

Test of Sample of upholstery fabric designated: Harald 3

Colour fastness to artificial light: Xenon arc fading lamp test

EN ISO 105-B02:2014 Method 2

1-8 scale, 8 best rating

Test apparatus: Atlas Ci4000 Xenon Weather-Ometer

Sample mark	Colour fastness
123	4
133	4
143	4
182	6-7
192	5-6
212	4-5
233	4
242	4-5
283	6-7
343	6
382	5-6
423	5
432	6
443	4
512	4-5
533	5-6
543	5-6
552	6
582	6
612	5-6



Colour fastness to artificial light: Xenon arc fading lamp test (continued)

Sample mark	Colour fastness
632	5
652	5
692	5
722	5
772	7
792	6
823	3
942	3-4
952	6
982	6

Test Report

Report Number:
127544-1-TEX



**DANISH
TECHNOLOGICAL
INSTITUTE**

Gregersensvej 1
DK-2630 Taastrup
+45 72 20 20 00
info@teknologisk.dk
www.teknologisk.dk

Page 1 of 4
Init.: CHF/LELN
Order no.: 127544
Encl.: 0

Assignor: KVADRAT A/S, Lundbergsvej 10, DK-8400 Ebeltoft

Material: Samples of upholstery fabric designated: Harald 3. See page 2 for detailed sample description.

Sampling: The assignor confirms having selected the product. The product was forwarded by the assignor and received at Danish Technological Institute on 4 March 2022.

Period: The test took place from 4 March 2022 to 25 March 2022.

Method: The test methods used are referenced in connection with the results. See page 4.

Test results: The results are shown on page 4.

Terms: This test was conducted accredited in accordance with international requirements (ISO/IEC 17025:2017) and in accordance with the General Terms and Conditions of Danish Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent.

Place: Danish Technological Institute, Taastrup, Environmental Technology

Signature: This document is only valid with a digital signature from Danish Technological Institute. The date of issue appears from the digital signature.

Charlotte Fischer
Senior Consultant



DIGITALLY SIGNED DOCUMENT

25 March 2022

DANISH TECHNOLOGICAL INSTITUTE









DANAK

TEST Reg.no. 2








Samples

Sample mark	Description	Photo
123	Sample of upholstery fabric Designated: Harald 3 Fibre content: 100% cotton	
133	Sample of upholstery fabric Designated: Harald 3 Fibre content: 100% cotton	
143	Sample of upholstery fabric Designated: Harald 3 Fibre content: 100% cotton	
182	Sample of upholstery fabric Designated: Harald 3 Fibre content: 100% cotton	
212	Sample of upholstery fabric Designated: Harald 3 Fibre content: 100% cotton	
242	Sample of upholstery fabric Designated: Harald 3 Fibre content: 100% cotton	



Samples (*continued*)

Sample mark	Description	Photo
233	Sample of upholstery fabric Designated: Harald 3 Fibre content: 100% cotton	
443	Sample of upholstery fabric Designated: Harald 3 Fibre content: 100% cotton	
512	Sample of upholstery fabric Designated: Harald 3 Fibre content: 100% cotton	
823	Sample of upholstery fabric Designated: Harald 3 Fibre content: 100% cotton	
942	Sample of upholstery fabric Designated: Harald 3 Fibre content: 100% cotton	



Results

Test of Samples of upholstery fabric designated: Harald 3

Colour fastness to artificial light: Xenon arc fading lamp test

EN ISO 105-B02:2014 Method 2

1-8 scale, 8 best rating

Test apparatus: Atlas Ci4000 Xenon Weather-Ometer

Sample mark	Colour fastness
123	5
133	4
143	4-5
182	6
212	5
242	5
233	4
443	4-5
512	4-5
823	4
942	4
